

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

THIS PAGE BLANK (USPTO)



Europäisches
Patentamt

Eur pean
Patent Office

Office eur péen
des brevets

REC'D 16 AUG 2000

WIPO PCT

PCI/EP000705899

10/019618

#24

EP00/5899

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

99810567.0

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts:
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

I.L.C. HATTEN-HECKMAN

DEN HAAG, DEN
THE HAGUE,
LA HAYE, LE

07/04/00

THIS PAGE BLANK (USPTO)



Eur päisches
Patentamt

Eur pean
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.:
Application no.: 99810567.0
Demande n°:

Anmeldetag:
Date of filing: 02/07/99
Date de dépôt:

Anmelder:
Applicant(s):
Demandeur(s):
Ciba Specialty Chemicals Holding Inc.
4057 Basel
SWITZERLAND

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:
Mono and multifunctional alkoxyamines

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:

/

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE
Etats contractants désignés lors du dépôt:

Bemerkungen:
Remarks:
Remarques:

THIS PAGE BLANK (USPTO)

Mono and Multifunctional Alkoxyamines

The present invention relates to compounds having at least one, preferably multiple alkoxyamine functionality, to their precursors and to a process for their preparation. Further objects of the invention are a composition comprising an ethylenically unsaturated monomer or oligomer and the alkoxyamine compound, a process for polymerization and the use of multifunctional alkoxyamines in radical polymerization processes.

The compounds of the present invention provide polymeric resin products having low polydispersity. The polymerization process proceeds with good monomer to polymer conversion efficiency. In particular, this invention relates to stable free radical-mediated polymerization processes which provide homopolymers, random copolymers, block copolymers, multiblock copolymers, graft copolymers and the like, at enhanced rates of polymerization and enhanced monomer to polymer conversions.

The multifunctional alkoxyamines of the present invention are particularly useful for the preparation of block copolymers, star (co)polymers, comb (co)polymers or other (co)polymers where a specific polymer architecture is desired.

By their multiple functionality they provide an ideal tool for tailor made polymerization processes.

Polymers or copolymers prepared by conventional free radical polymerization processes inherently have broad molecular weight distributions or polydispersities which are generally higher than about four. If a free radical polymerization process is to be used for producing narrow molecular weight distributions, then all polymer chains must be initiated at about the same time and termination of the growing polymer-chains by combination or disproportionation processes must be avoided.

Conventional radical polymerization reaction processes pose various significant problems, such as difficulties in predicting or controlling the molecular weight, the polydispersity and the modality of the polymers produced. Furthermore, free radical polymerization processes in bulk of the prior art are difficult to control because the polymerization reaction is strongly exothermic and an efficient heat removal in the highly viscous polymer is mostly impossible.

- 2 -

The exothermic nature of the prior art free radical polymerization processes often severely restricts the concentration of reactants or the reactor size upon scale-up.

Due to the above mentioned uncontrollable polymerization reactions, gel formation in conventional free radical polymerization processes are also possible and cause broad molecular weight distributions and/or difficulties during filtering, drying and manipulating the product resin.

US-A-4 581 429 to Solomon et al., issued April 8, 1986, discloses a free radical polymerization process which controls the growth of polymer chains to produce short chain or oligomeric homopolymers and copolymers, including block and graft copolymers. The process employs an initiator having the formula (in part) $R'R''N-O-X$, where X is a free radical species capable of polymerizing unsaturated monomers. The reactions typically have low conversion rates. Specifically mentioned radical $R'R''N-O\bullet$ groups are derived from 1,1,3,3 tetraethylisindoline, 1,1,3,3 tetrapropylisindoline, 2,2,6,6 tetramethylpiperidine, 2,2,5,5 tetramethylpyrrolidine or di-t-butylamine. However, the suggested compounds do not fulfill all requirements. Particularly the polymerization of acrylates does not proceed fast enough and/or the monomer to polymer conversion is not as high as desired.

US 5 627 248 and US 5 677 388 disclose difunctional alkoxyamines which contain additionally a cleaving bond, through which they can act as radical initiators such as for example azo initiators, disulfide initiators, peroxide initiators and sulfur containing chain transfer agents.

However there is still a need for polymerization processes and for the preparation of narrow polydispersity polymeric resins with defined molecular weights using the economical free radical polymerization techniques. These polymerization processes will also control the physical properties of the polymers such as viscosity, hardness, gel content, processability, clarity, high gloss, durability and the like.

The initiators/regulators, the polymerization processes and resin products of the present invention are useful in many applications, including a variety of specialty applications, such as for the preparation of block copolymers which are useful as compatibilizing agents for polymer blends, or dispersing agents for coating systems or for the preparation of narrow molecular weight resins or oligomers for use in coating technologies and thermoplastic films


- 3 -

or as toner resins and liquid immersion development ink resins or ink additives used for electrophotographic imaging processes.


Surprisingly, it has now been found that the present compounds are very suitable to prepare (co)polymers particularly block, star, comb (co)polymers and the like.

Polymerization of the monomers results in a polymer or copolymer of narrow polydispersity and a high monomer to polymer conversion even at relatively low temperatures and at short reaction times, making the polymerization process particularly suitable for industrial applications. The resulting (co)polymers are of high purity and in many cases colorless, therefore not requiring any further purification.

One object of the present invention is a compound of formula (I) or (II)



(I)



(II)

wherein

R_1 and R_2 are independently of each other hydrogen, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl or phenyl which are unsubstituted or substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

A is a group capable of forming a stable free nitroxyl radical $A\bullet$, which is bound via its oxygen atom to the carbon atom;

Y is O, NR_3 or CHR_3-X_a , wherein X_a is O, S or NR_3 ;

R_3 is hydrogen, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl or phenyl which are unsubstituted or substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

Q_1 is an organic or inorganic radical, derived from a compound having at least one functional group being capable of reacting with a hydroxy group;

Q_2 is an organic radical derived from a mono or polyfunctional alcohol, mono or polyfunctional aminoalcohol, mono or polyfunctional amine mono or polyfunctional mercaptane, mono or polyfunctional phenol or mono or polyfunctional thiophenol; and

- 4 -

n is a number from 1 to 20;

with the proviso, that if R_1 is H and R_2 is $-\text{CH}_2\text{-O-tert.butyl}$, A is not 2,2,6,6-tetramethylpiperidine or 2,2,6,6-tetramethylpiperidine-4-carboxylic acid.




Q_1 in the meaning of an inorganic radical is for example a halogenated inorganic acid derivative.

Preferably Q_1 is derived from an unsubstituted or substituted triazine, from a mono or multifunctional alkylating agent, from a mono or polycarboxylic acid or acid derivative, from a mono or polyepoxide, from a mono or polyisocyanate or from POCl_3 , SO_2Cl_2 , BCl_3 or SiCl_4 .

Examples for Q_1 are given below.

a) Examples for mono- or multifunctional triazines are:


tri-, di-, oder mono-chlorotriazine



wherein R_1 and R_6 are $\text{C}_1\text{-C}_{18}$ alkyl, -phenyl, $\text{C}_1\text{-C}_{18}$ alkoxy, $\text{C}_1\text{-C}_{18}$ alkylthio, phenoxy, $\text{NH}(\text{C}_1\text{-C}_{18}\text{alkyl})$, $\text{N}(\text{di-C}_1\text{-C}_{18}\text{alkyl})$ or thiophenyl. It is also possible to use the corresponding fluoro-triazines instead of chloro-triazines.

b) Alkylating agents are in principal known. Examples for mono- and multifunctional alkylating agents are :

- 5 -



wherein X is a leaving group such as for example halogen, an aliphatic or aromatic sulfonate such as toluene sulfonate or methane sulfonate;

Y_1 is O, NH or N(C₁-C₁₈)alkyl; and

k and n_a are numbers from 1 to 10, n_b is a number from 1 to 20; and

R_0 may be any aromatic or aliphatic substituent, such as for example unsubstituted or substituted C₁-C₁₈alkyl or phenyl.

Also suitable is allylchloride as alkylating agent, leading to an allyl group as Q₁.

c) Examples for mono, di- and polycarboxylic acids bzw. acid chlorides, anhydrides or esters are:

Aliphatic mono carboxylic acids or their derivatives, which can contain 2 to 20 carbon atoms. Typical examples are acetic acid, acetyl chloride, acetic acid anhydride, propionic acid and derivatives, stearic acid, lauric acid and the corresponding derivatives.

The aliphatic dicarboxylic acids can contain 2 to 40 carbon atoms, the cycloaliphatic dicarboxylic acids 6 to 10 carbon atoms, the aromatic dicarboxylic acids 8 to 14 carbon atoms, the aliphatic hydroxycarboxylic acids 2 to 12 carbon atoms and the aromatic and cycloaliphatic hydroxycarboxylic acids 7 to 14 carbon atoms.

Suitable dicarboxylic acids are linear and branched saturated aliphatic dicarboxylic acids, aromatic dicarboxylic acids and cycloaliphatic dicarboxylic acids.

- 6 -

Suitable aliphatic dicarboxylic acids are those containing 2 to 40 carbon atoms, for example oxalic acid, malonic acid, dimethylmalonic acid, succinic acid, pimelic acid, adipic acid, trimethyladipic acid, sebacic acid, azelaic acid and dimeric acids (dimerisation products of unsaturated aliphatic carboxylic acids such as oleic acid), alkylated malonic and succinic acids, such as octadecylsuccinic acid.

Suitable cycloaliphatic dicarboxylic acids are: 1,3-cyclobutanedicarboxylic acid, 1,3-cyclopentanedicarboxylic acid, 1,3- and 1,4-cyclohexanedicarboxylic acid, 1,3- and 1,4-(dicarboxymethyl)cyclohexane, 4,4'-dicyclohexyldicarboxylic acid.

Suitable aromatic dicarboxylic acids are: in particular terephthalic acid, isophthalic acid, o-phthalic acid, and 1,3-, 1,4-, 2,6- or 2,7-naphthalenedicarboxylic acid, 4,4'-diphenyldicarboxylic acid, 4,4'-diphenylsulfonedicarboxylic acid, 4,4'-benzophenonedicarboxylic acid, 1,1,3-trimethyl-5-carboxyl-3-(p-carboxylphenyl)indane, 4,4'-diphenyletherdicarboxylic acid, bis-p-(carboxylphenyl)methane or bis-p-(carboxylphenyl)ethane.

Examples for more than difunctional acids are trimellitic acid, citric acid, pyromellitic acid or itaconic acid.

The above carboxylic acids and acid derivatives are also examples for the substituent R in formula (XXXA) defined hereinafter.

d) Examples of reactive derivatives of inorganic acids are POCl_3 , SO_2Cl_2 , SiCl_4 which leads

for example to compounds such as

$$\left[\begin{array}{c} \text{R1} \\ | \\ \text{A} - \text{C} - \text{C}_6\text{H}_4 - \text{O} \\ | \\ \text{R2} \end{array} \right]_3 \text{P}=\text{O}$$

e) The epoxy compounds which can be used in the context of the invention may have an aliphatic, aromatic, cycloaliphatic, araliphatic or heterocyclic structure; they include epoxy groups as side groups. The epoxy groups are preferably attached to the rest of the molecule as glycidyl groups by way of ether or ester linkages, or else the compounds are N-glycidyl derivatives of heterocyclic amines, amides or imides. Epoxy compounds of these types are widely known and are obtainable commercially.

- 7 -

They lead for example to compounds such as
$$A-\begin{matrix} R1 \\ | \\ -C- \\ | \\ R2 \end{matrix}-\text{C}_6\text{H}_4-\text{O}-\left[\begin{matrix} \text{OH} \\ | \\ \text{CH}-R''' \end{matrix} \right]_n$$
, wherein

R''' denotes an organic radical derived from the corresponding epoxy compound and n is as defined above. The epoxy compounds comprise epoxy radicals, especially those of the

formula
$$\begin{matrix} \text{H} \\ | \\ -\text{C}- \\ | \\ R' \end{matrix}-(\text{CH}_2)_{n_e}-\begin{matrix} \text{O} \\ \diagup \quad \diagdown \\ \text{C} \quad \text{C} \\ | \quad | \\ R'' \quad R''' \end{matrix}$$
, which are attached directly to carbon, oxygen, nitrogen

or sulfur atoms and in which R' and R''' are both hydrogen, R'' is hydrogen or methyl and n_e is 0, or in which R' and R''' together are -CH₂-CH₂- or -CH₂-CH₂-CH₂-, R'' in that case is hydrogen, and n_e is 0 or 1.

Examples of epoxy compounds that may be mentioned are:

1) Polyglycidyl esters and poly(β-methylglycidyl) esters obtainable by reacting a compound having at least two carboxyl groups in the molecule with epichlorohydrin and/or glyceroldichlorohydrin and/or β-methylepichlorohydrin. The reaction is judiciously carried out in the presence of bases.

Compounds having at least two carboxyl groups in the molecule that can be used are aliphatic polycarboxylic acids. Examples of these polycarboxylic acids are glutaric, adipic, pimelic, suberic, azelaic, sebacic or dimerized or trimerized linoleic acid.

Alternatively, cycloaliphatic polycarboxylic acids can be employed, examples being tetrahydrophthalic, 4-methyltetrahydrophthalic, hexahydrophthalic or 4-methylhexahydrophthalic acid.

It is also possible to use aromatic polycarboxylic acids, such as phthalic, isophthalic, trimellitic and pyromellitic acid.

Likewise employable are carboxyl-terminated adducts of, for example, trimellitic acid and polyols such as glycerol or 2,2-bis(4-hydroxycyclohexyl)propane.

II) Polyglycidyl ethers or poly(β -methylglycidyl) ethers obtainable by reacting a compound having at least two free alcoholic hydroxyl groups and/or phenolic hydroxyl groups with a suitably substituted epichlorohydrin under alkaline conditions or in the presence of an acidic catalyst with subsequent alkali treatment.

Ethers of this type are derived, for example, from acyclic alcohols, such as ethyleneglycol, diethyleneglycol and higher poly(oxyethylene) glycols, propane-1,2-diol, or poly(oxypropylene) glycols, propane-1,3-diol, butane-1,4-diol, poly(oxytetramethylene) glycols, pentane-1,5-diol, hexane-1,6-diol, hexane-2,4,6-triol, glycerol, 1,1,1-trimethylolpropane, bis-trimethylolpropane, pentaerythritol, sorbitol, and from polyepichlorohydrins.

They are alternatively derived, for example, from cycloaliphatic alcohols, such as 1,3- or 1,4-dihydroxycyclohexane, bis(4-hydroxycyclohexyl)methane, 2,2-bis(4-hydroxycyclohexyl)propane or 1,1-bis(hydroxymethyl)cyclohex-3-ene, or they possess aromatic nuclei, such as N,N-bis(2-hydroxyethyl)aniline or p,p'-bis(2-hydroxyethylamino)diphenylmethane.

The epoxy compounds may also be derived from mononuclear phenols, such as resorcinol or hydroquinone; or else they are based on polynuclear phenols, such as on bis(4-hydroxyphenyl)methane, 2,2-bis(4-hydroxyphenyl)propane, 2,2-bis(3,5-dibromo-4-hydroxyphenyl)propane or 4,4'-dihydroxydiphenyl sulfone, or on condensates of phenols with formaldehyde that are obtained under acidic conditions, such as phenol novolaks.

III) Poly(N-glycidyl) compounds obtainable by dehydrochlorinating the reaction products of epichlorohydrin with amines containing at least two amino hydrogen atoms. These amines are, for example, aniline, toluidine, n-butylamine, bis(4-aminophenyl)methane, m-xylylenediamine or bis(4-methylaminophenyl)methane, and also N,N,O-triglycidyl-m-aminophenol or N,N,O-triglycidyl-p-aminophenol.

The poly(N-glycidyl) compounds also include N,N'-diglycidyl derivatives of cycloalkyleneureas, such as ethyleneurea or 1,3-propyleneurea, and N,N'-diglycidyl derivatives of hydantoins, such as of 5,5-dimethylhydantoin.

IV) Poly(S-glycidyl) compounds, such as di-S-glycidyl derivatives derived from dithiols, such as ethane-1,2-dithiol or bis(4-mercaptomethylphenyl) ether.

- 9 -

V) Epoxy compounds in which R' and R''' together are -CH₂-CH₂- and n_e is 0 are bis(2,3-epoxycyclopentyl) ether, 2,3-epoxycyclopentyl glycidyl ether or 1,2-bis(2,3-epoxycyclopentyl-oxy) ethane. An example of an epoxy resin having a radical of the formula in which R' and R''' together are -CH₂-CH₂- and n_e is 1 is (3,4-epoxy-6-methylcyclohexyl)methyl 3',4'-epoxy-6'-methylcyclohexanecarboxylate.

f) Mono and polyfunctional isocyanates are well known and a wide variety is commercially

available. The isocyanates lead to the following structure

$$\text{A} - \begin{array}{c} \text{R1} \\ | \\ \text{C} \\ | \\ \text{R2} \end{array} - \text{C}_6\text{H}_4 - \text{O} - \left[\begin{array}{c} \text{O} \\ || \\ \text{C} - \text{N} - \text{R}'''' \\ | \\ \text{H} \end{array} \right]_n$$

wherein R'''' denotes an aliphatic or aromatic organic radical derived from the isocyanate compound and n is as defined above.

Examples of isocyanates are di-, tri- or tetra isocyanates. Diisocyanates are widely used in the industry and most of them are commercially available. Preferred diisocyanates are those in which the bridge group between the isocyanate groups is formed by a linear or branched aliphatic C₂-C₂₀alkyl which is unsubstituted or mono- or polysubstituted by C₁-C₆ alkyl or C₁-C₆alkoxy, C₃-C₈cycloalkyl or heterocycloalkyl which is unsubstituted or mono- or polysubstituted by C₁-C₆alkyl or C₁-C₆alkoxy, linear or branched aliphatic C₂-C₂₀alkyl which is interrupted by unsubstituted or C₁-C₆alkyl- or C₁-C₆alkoxy-substituted C₃-C₈cycloalkyl or heterocycloalkyl and is unsubstituted or substituted by C₁-C₆alkyl or C₁-C₆alkoxy, phenyl, naphthyl, biphenyl or C₃-C₁₀heteroaryl which is unsubstituted or mono- or polysubstituted by C₁-C₆alkyl or C₁-C₆alkoxy, or linear or branched aliphatic C₂-C₂₀alkyl which is interrupted by phenyl, naphthyl or C₃-C₁₀heteroaryl and is unsubstituted or substituted by C₁-C₆alkyl or C₁-C₆alkoxy

The linear or branched C₁-C₂₀alkyl radicals are, for example, methyl, ethyl and the various position isomers of propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl or hexadecyl, heptadecyl, octadecyl, nonadecyl or eicosyl.

The C₁-C₆alkoxy radicals can be linear or branched and are, for example, methoxy, ethoxy and the various positional isomers of propoxy, butoxy, pentoxy or hexoxy.

Heterocycloalkyl is, for example, pyrrolidine, piperidine, morpholine, oxazolidine, dioxolane, or an isocyanuric acid triester group.

C₃-C₈cycloalkyl is, for example, cyclopropyl, dimethylcyclopropyl, cyclobutyl, cyclopentyl, methylcyclopentyl, cyclohexyl, cycloheptyl or cyclooctyl.

Aromatic means, for example, phenyl, naphthyl or anthracenyl.

Heteroaromatic means, for example, pyridine, pyrimidine, pyrrole, furan, imidazole, pyrazole or triazine.

Specific examples of diisocyanates are 1,6-bis[isocyanato]hexane, 5-isocyanato-3-(isocyanatomethyl)-1,1,3-trimethylcyclohexane, 1,3-bis[5-isocyanato-1,3,3-trimethyl-phenyl]-2,4-dioxo-1,3-diazetidines, 3,6-bis[9-isocyanatononyl]-4,5-di(1-heptenyl)cyclohexene, bis[4-isocyanatocyclohexyl]methane, trans-1,4-bis[isocyanato]cyclohexane, 1,3-bis[bis(isocyanatomethyl)benzene], 1,3-bis[1-isocyanato-1-methylethyl]benzene, 1,4-bis[2-isocyanatoethyl]cyclohexane, 1,3-bis[isocyanatomethyl]cyclohexane, 1,4-bis[1-isocyanato-1-methylethyl]benzene, bis[isocyanato]isododecylbenzene, 1,4-bis[isocyanato]benzene, 2,4-bis[isocyanato]toluene, 2,6-bis[isocyanato]toluene, 2,4-/2,6-bis[isocyanato]toluene, 2-ethyl-1,2,3-tris[3-isocyanato-4-methylanilinocarbonyloxy]propane, N,N'-bis[3-isocyanato-4-methylphenyl]urea, 1,4-bis[3-isocyanato-4-methylphenyl]-2,4-dioxo-1,3-diazetidine, 1,3,5-tris[3-isocyanato-4-methylphenyl]-2,4,6-trioxohexahydro-1,3,5-triazine, 1,3-bis[3-isocyanato-4-methylphenyl]-2,4,5-trioximidazolidine, bis[2-isocyanatophenyl]methane, (2-isocyanatophenyl)(4-isocyanato-phenyl)methane, bis[4-isocyanatophenyl]methane, 2,4-bis[4-isocyanatobenzyl]-1-isocyanatobenzene, 4-isocyanato-3-(4-isocyanatobenzyl)-phenyl[[2-isocyanato-5-(4-isocyanatobenzyl)phenyl]methane], tris[4-isocyanatophenyl]methane, 1,5-bis[isocyanato]naphthalene, or 4,4'-bis[isocyanato]-3,3'-dimethylbiphenyl.

- 11 -

Q₂ is an organic radical derived from a mono or polyfunctional alcohol, mono or polyfunctional aminoalcohol, mono or polyfunctional amine, mono or polyfunctional mercaptane, mono or polyfunctional phenol or mono or polyfunctional thiophenol.

The aliphatic mono or polyfunctional alcohol can contain 2 to 12 carbon atoms, the cycloaliphatic polyols 5 to 8 carbon atoms and the aromatic polyols 6 to 16 carbon atoms.

Polyoxyalkylene glycols having a molecular weight from 150 to 40000 can also be used.

Aromatic polyols are those, wherein at least two hydroxyl groups are bound to one or to different aromatic hydrocarboxylic radicals.


Suitable aliphatic polyols are for example diols which are linear or branched aliphatic glycols, in particular those containing 2 to 12, preferably 2 to 6, carbon atoms in the molecule, for example: ethylene glycol, 1,2- and 1,3-propylene glycol, 1,2-, 1,3-, 2,3- or 1,4-butanediol, pentyl glycol, neopentyl glycol, 1,6-hexanediol, 1,12-dodecanediol. A suitable cycloaliphatic diol is, for example, 1,4-dihydroxycyclohexane. Other suitable aliphatic diols are, for example, 1,4-bis(hydroxymethyl)cyclohexane, aromatic-aliphatic diols, such as p-xylylene glycol or 2,5-dichloro-p-xylylene glycol, 2,2-(β -hydroxyethoxyphenyl)propane and polyoxyalkylene glycols, such as diethylene glycol, triethylene glycol, polyethylene glycol or polypropylene glycol. The alkylenediols are preferably linear and preferably contain 2 to 4 carbon atoms.

Other suitable aliphatic diols are the β -hydroxyalkylated, in particular β -hydroxyethylated bisphenols, such as 2,2-bis[4'-(β -hydroxyethoxy)phenyl]propane.

Another group of suitable aliphatic diols are the heterocyclic diols described in the German published patent specifications 1812003, 2342432, 2342372 and 2453326. Examples are: N,N'-bis(β -hydroxyethyl)-5,5-dimethylhydantoin, N,N'-bis(β -hydroxypropyl)-5,5-dimethylhydantoin, methylenebis-[N-(β -hydroxyethyl)-5-methyl-5-ethylhydantoin], methylenebis-[N-(β -hydroxyethyl)-5,5-dimethylhydantoin], N,N'-bis(β -hydroxyethyl)benzimidazolone, N,N'-bis(β -hydroxyethyl)-(tetrachloro)benzimidazolone or N,N'-bis(β -hydroxyethyl)-(tetrabromo)benzimidazolone.

Suitable aromatic diols are mononuclear diphenols and, in particular, dinuclear diphenols carrying a hydroxyl group at each aromatic nucleus. The term aromatic will be taken to mean preferably hydrocarbonaromatic radicals such as phenylene or naphthylene. Besides e.g. hydroquinone, resorcinol or 1,5-, 2,6- and 2,7-dihydroxynaphthalene, bisphenols merit particular mention.

A suitable triol is for example



Examples of bisphenols are: bis(p-hydroxyphenyl) ether or bis(p-hydroxyphenyl) thioether, bis(p-hydroxyphenyl)sulfone, bis(p-hydroxyphenyl)methane, bis(4-hydroxyphenyl)-2,2'-biphenyl, phenylhydroquinone, 1,2-bis(p-hydroxyphenyl)ethane, 1-phenyl-bis(p-hydroxyphenyl)-methane, diphenyl-bis(p-hydroxyphenyl)methane, diphenyl-bis(p-hydroxyphenyl)ethane, bis-(3,5-dimethyl-4-hydroxyphenyl)sulfone, bis(3,5-dimethyl-4-hydroxyphenyl)-p-diisopropylbenzene, bis(3,5-dimethyl-4-hydroxyphenyl)-m-diisopropylbenzene, 2,2-bis(3',5'-dimethyl-4'-hydroxyphenyl)propane, 1,1'- or 2,2-bis(p-hydroxyphenyl)butane, 2,2-bis(p-hydroxyphenyl)hexafluoropropane, 1,1-dichloro- or 1,1,1-trichloro-2,2-bis(p-hydroxyphenyl)ethane, 1,1-bis(p-hydroxyphenyl)cyclopentane and, in particular, 2,2-bis(p-hydroxyphenyl)propane (bisphenol-A) and 1,1-bis(p-hydroxyphenyl)cyclohexane (bisphenol-C).

The polyaminoalcohols or polyamines can be deduced from the above mentioned polyalcohols by replacing one or more hydroxyl groups by amino groups.

Examples of other polyalcohols are erythrose, threose or are derived from hexoses or pentoses, such as glucose, fructose, mannose, galactose, talose, allose, altrose, xylose, lyxose, ribose or arabinose or their corresponding reduced forms.

Suitable mercaptanes or thiophenols are those which are derived by substituting the oxygen atom by a sulfur atom in the above mentioned examples.

Preferred is a compound of formula (I) or (II), wherein R_1 and R_2 are independently of each other hydrogen, C_1 - C_{12} alkyl, C_3 - C_{12} alkenyl or phenyl.

- 13 -

More preferably R_1 and R_2 are independently of each other hydrogen or C_1 - C_4 alkyl, most preferably hydrogen or methyl.

Preferred is a compound of formula (II), wherein Y is O or NR_3 .

More preferred is a compound of formula (II) wherein Y is O.

Also preferred is a compound of formula (I) or (II), wherein n is a number from 2-10, more preferably from 2-6 and most preferably from 2-4.

Preferably Q_1 is an organic radical derived from an unsubstituted or substituted triazine, from a mono or polycarboxylic acid or acid derivative, from a mono or multifunctional alkylating agent or from a mono or polyisocyanate.

More preferably Q_1 is an organic radical derived from an unsubstituted or substituted triazine, from a polycarboxylic acid or polycarboxylic acid derivative, having 2-6 carboxylgroups, from a multifunctional alkylating agent having 2-6 functional groups or from a polyisocyanate, having 2-6 isocyanate groups.

Examples for Q_1 have already been mentioned.

Preferably Q_2 is an organic radical derived from a polyfunctional alcohol, a polyfunctional aminoalcohol or a polyfunctional amine.


More preferably Q_2 is a radical derived from a polyalcohol having 2-6 hydroxy groups, a polyaminoalcohol having 2-6 amino and/or hydroxy groups, or a polyamine having 2-6 amine groups.

Examples for Q_2 have already been mentioned.

The radical $A\bullet$ derived from the group A can be a stable open chain nitroxyl radical or a cyclic nitroxyl radical.

Preferred is a stable cyclic nitroxyl radical.

In formula (I) or (II) A is preferably a group of formula (X)



wherein n_1 is 0 or 1

R_{101} , R_{102} , R_{103} are each independently of one another hydrogen, halogen, NO_2 , cyano, $-\text{CONR}_{105}\text{R}_{106}$, $-(\text{R}_{109})\text{COOR}_{104}$, $-\text{C}(\text{O})-\text{R}_{107}$, $-\text{OR}_{108}$, $-\text{SR}_{108}$, $-\text{NHR}_{108}$, $-\text{N}(\text{R}_{108})_2$, carbamoyl, $\text{di}(\text{C}_1\text{-C}_{18}\text{alkyl})\text{carbamoyl}$, $-\text{C}(\equiv\text{NR}_{105})(\text{NHR}_{106})$; unsubstituted $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkenyl}$, $\text{C}_2\text{-C}_{18}\text{alkynyl}$, $\text{C}_7\text{-C}_9\text{phenylalkyl}$, $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ or $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ containing at least one nitrogen or oxygen atom; or $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkenyl}$, $\text{C}_2\text{-C}_{18}\text{alkynyl}$, $\text{C}_7\text{-C}_9\text{phenylalkyl}$, $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ or $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ containing at least one nitrogen or oxygen atom, which are substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, $\text{C}_1\text{-C}_4\text{alkoxy}$, $\text{C}_1\text{-C}_4\text{alkylthio}$, $\text{C}_1\text{-C}_4\text{alkylamino}$ or $\text{di}(\text{C}_1\text{-C}_4\text{alkyl})\text{amino}$; or phenyl, which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$, $\text{C}_1\text{-C}_4\text{alkoxy}$, $\text{C}_1\text{-C}_4\text{alkylthio}$, halogen, cyano, hydroxy, carboxy, $\text{C}_1\text{-C}_4\text{alkylamino}$ or $\text{di}(\text{C}_1\text{-C}_4\text{alkyl})\text{amino}$; or R_{102} and R_{103} , together with the linking carbon atom, form a $\text{C}_3\text{-C}_{12}$ cycloalkyl radical, a $(\text{C}_4\text{-C}_{12}\text{ cycloalkanon})\text{-yl}$ radical or a $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ radical containing at least one O atom and/or a NR_{108} group; or if n_1 is 1



R_{104} is hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$, phenyl, an alkali metal cation or a tetraalkylammonium cation; R_{105} and R_{106} are hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkyl}$ which is substituted by at least one hydroxy group or, taken together, form a $\text{C}_2\text{-C}_{12}\text{alkylene}$ bridge or a $\text{C}_2\text{-C}_{12}\text{-alkylene}$ bridge interrupted by at least one O or/and NR_{108} atom; R_{107} is hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$ or phenyl;

- 15 -

R₁₀₈ is hydrogen, C₁-C₁₈alkyl or C₂-C₁₈alkyl which is substituted by at least one hydroxy group;

R₁₀₉ is C₁-C₁₂alkylen or a direct bond;

R₁₁₀ is C₄-C₁₈alkyl bound via a tertiary C-atom to the nitrogen atom, C₉-C₁₁phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or C₄-C₁₈alkyl bound via a tertiary C-atom to the nitrogen atom, C₉-C₁₁phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; if n₁ is 1

R₁₁₁ is C₁-C₁₈alkyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or

C₁-C₁₈alkyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or a polycyclic cycloaliphatic ring system or a polycyclic cycloaliphatic ring system with at least one di- or trivalent nitrogen atom; or

R₁₁₀ and R₁₁₁ together form a C₂-C₁₂alkylene bridge, a C₃-C₁₂alkylen-on bridge or a C₂-C₁₂alkylene bridge which is interrupted by at least one O or N atom, which bridges are unsubstituted or substituted with C₁-C₁₈alkyl, hydroxy(C₁-C₄)alkyl, phenyl, C₇-C₉phenylalkyl, NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino,

R₁₁₂ is hydrogen, -(R₁₀₉)COOR₁₀₄, cyano, -OR₁₀₈, -SR₁₀₈, -NHR₁₀₈, -N(R₁₀₈)₂, -NH-C(O)-R₁₀₈, unsubstituted C₁-C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or




C₁-C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or

phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino, di(C₁-C₄alkyl)amino; or

R₁₁₁ and R₁₁₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

- 16 -

or A is a group of formula XXa, XXb or XXc



wherein

Y_1 is O or CH_2 ;

Q is O or NR_{220} , wherein R_{220} is hydrogen or C_1 - C_{18} alkyl;

R_{201} is tertiary C_4 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$, wherein R_{221} is hydrogen, an alkali metal atom or C_1 - C_{18} alkyl and R_{222} is C_1 - C_{18} alkyl; or

R_{201} is C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, a polycyclic alkyl radical or a polycyclic alkyl radical which is interrupted by at least one O or N atom;

R_{202} and R_{203} are independently C_1 - C_{18} alkyl, benzyl, C_5 - C_{12} cycloalkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$ or together with the carbon atom form a C_5 - C_{12} cycloalkyl ring;

if Y_1 is O,

R_{204} and R_{212} are OH, O(alkali-metal) C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently from each other hydrogen, C_1 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

if Y_1 is CH_2 ,

R_{204} is OH, C_1 - C_{18} alkoxy, benzyloxy, $O-C(=O)-(C_1-C_{18})$ alkyl or $NR_{223}R_{224}$;

R_{212} are a group $C(O)R_{225}$, wherein R_{225} is OH, C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently from each other hydrogen, C_1 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

R_{205} , R_{206} , R_{207} and R_{208} are independently of each other C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl or phenyl; or


- 17 -

R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_{12} cycloalkyl ring;

R_{209} and R_{210} are independently of each other hydrogen, formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, benzyl or phenyl which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

R_{211} , is formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, benzyl or phenyl which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

or A is a group containing a structural element of formula (XXX)





(XXX), wherein

G_1 , G_2 , G_3 , G_4 are independently C_1 - C_6 alkyl or G_1 and G_2 or G_3 and G_4 , or G_1 and G_2 and G_3 and G_4 together form a C_5 - C_{12} cycloalkyl group;

G_5 , G_6 independently are H, C_1 - C_{18} alkyl, phenyl, naphthyl or a group $COOC_1$ - C_{18} alkyl

- 18 -

or A is a group of formula (XLa) or (XLb).



R_{301} , R_{302} , R_{303} and R_{304} independently of each other are C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, or C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by OH, halogen or a group $-O-C(O)-R_{305}$, C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_{305} group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl or R_{301} and R_{302} and/or R_{303} and R_{304} together with the linking carbon atom form a C_3 - C_{12} cycloalkyl radical;

R_{305} , R_{306} and R_{307} independently are hydrogen, C_1 - C_{18} alkyl or C_6 - C_{10} aryl;

Z_1 is O or NR_{308} ;

R_{308} is hydrogen, OH, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by one or more OH, halogen or a group $-O-C(O)-R_{305}$, C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_{305} group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl, C_7 - C_9 phenylalkyl, C_5 - C_{10} heteroaryl, $-C(O)-C_1$ - C_{18} alkyl, $-O-C_1$ - C_{18} alkyl or $-COOC_1$ - C_{18} alkyl;

Q_4 is a direct bond or a divalent radical $CR_{309}R_{310}$, $CR_{309}R_{310}-CR_{311}R_{312}$,

$CR_{309}R_{310}CR_{311}R_{312}CR_{313}R_{314}$, $C(O)$ or $CR_{309}R_{310}C(O)$, wherein R_{309} , R_{310} , R_{311} , R_{312} , R_{313} and R_{314} are independently hydrogen, phenyl or C_1 - C_{18} alkyl.

Halogen is Fluorine, Chlorine, Bromine or Iodine, preferably Chlorine or Bromine.

The alkyl radicals in the various substituents may be linear or branched. Examples of alkyl containing 1 to 18 carbon atoms are methyl, ethyl, propyl, isopropyl, butyl, 2-butyl, isobutyl, t-

- 19 -

butyl, pentyl, 2-pentyl, hexyl, heptyl, octyl, 2-ethylhexyl, t-octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, hexadecyl and octadecyl.

C₅-C₁₂cycloalkyl is typically, cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl.

Cycloalkyl which is interrupted by at least one O or N atom is for example 2-tetrahydropyran-yl, tetrahydrofurane-yl, 1,4 dioxan-yl, pyrrolidin-yl, tetrahydrothiophen-yl, pyrazolidin-yl, imidazolidin-yl, butyrolactone-yl, caprolactame-yl

Examples for alkali metal are lithium, sodium or potassium.

Alkyl substituted by-OH is typically 2-hydroxyethyl, 2-hydroxypropyl or 2-hydroxybutyl.

C₁-C₁₈ alkoxy is for example methoxy, ethoxy, propoxy, butoxy, pentoxy, octoxy, dodecyloxy or octadecyloxy.

C₁-C₁₈Alkyl substituted by C₁-C₈alkoxy, preferably by C₁-C₄alkoxy, in particular by methoxy or ethoxy, is typically 2-methoxyethyl, 2-ethoxyethyl, 3-methoxypropyl, 3-ethoxypropyl, 3-butoxypropyl, 3-octoxypropyl and 4-methoxybutyl.

C₁-C₁₈Alkyl substituted by di(C₁-C₄alkyl)amino is preferably e.g. dimethylamino, diethylamino, 2-dimethylaminoethyl, 2-diethylaminoethyl, 3-dimethylaminopropyl, 3-diethylaminopropyl, 3-dibutylaminopropyl and 4-diethylaminobutyl.

C₁-C₁₈Alkyl substituted by C₁-C₄alkylamino is preferably e.g. methylamino, ethylamino, 2-methylaminoethyl, 2-ethylaminoethyl, 3-methylaminopropyl, 3-ethylaminopropyl, 3-butylaminopropyl and 4-ethylaminobutyl.

C₁-C₄Alkylthio is typically thiomethyl, thioethyl, thiopropyl, thioisopropyl, thiobutyl and thioisobutyl.

C₂-C₁₈ alkylcarbonyl is for example acetyl, propionyl, butyryl, pentylcarbonyl, hexylcarbonyl or dodecylcarbonyl.

- 20 -

C₇-C₉phenylalkyl is for example benzyl, phenylethyl or phenylpropyl.

C₃-C₁₈alkyl interrupted by at least one O atom is for example -CH₂-CH₂-O-CH₂-CH₃, -CH₂-CH₂-O-CH₃ or -CH₂-CH₂-O-CH₂-CH₂-CH₂-O-CH₂-CH₃. It is preferably derived from polyethylene glycol. A general description is -((CH₂)_a-O)_b-H/CH₃, wherein a is a number from 1 to 6 and b is a number from 2 to 10.

Examples of C₂-C₁₂alkylene bridges, preferably of C₂-C₆alkylene bridges, are ethylene, propylene, butylene, pentylene, hexylene.

C₂-C₁₂alkylene bridges interrupted by at least one N or O atom are, for example, -CH₂-O-CH₂-CH₂-, -CH₂-O-CH₂-CH₂-CH₂-, -CH₂-O-CH₂-CH₂-CH₂-CH₂-, -CH₂-O-CH₂-CH₂-O-CH₂-, -CH₂-NH-CH₂-CH₂-, -CH₂-NH-CH₂-CH₂-CH₂-, -CH₂-NH-CH₂-CH₂-CH₂-CH₂-, -CH₂-NH-CH₂-CH₂-NH-CH₂- or -CH₂-NH-CH₂-CH₂-O-CH₂-.

Examples for C₄-C₁₂cycloalkanone-yl are cyclopentanone-yl, cyclohexanone-yl or cycloheptanone-yl.

Phenyl substituted by 1, 2 or 3 C₁-C₄alkyl or C₁-C₄alkoxy is typically methylphenyl, dimethylphenyl, trimethylphenyl, t-butylphenyl, di-t-butylphenyl, 3,5-di-t-butyl-4-methylphenyl, methoxyphenyl, ethoxyphenyl and butoxyphenyl.

Examples of polycyclic cycloaliphatic ring systems are adamantane, cubane, twistane, norbornane, bicyclo[2.2.2]octane or bicyclo[3.2.1]octane.

An example of a polycyclic heterocycloaliphatic ring system is hexamethylenetetramine (urotropine).

Examples of monocarboxylic acids with 1 to 18 carbon atoms are formic acid, acetic acid, propionic acid, phenyl acetic acid, cyclohexane-carbonic acid, mono-, di- and trichloroacetic acid or mono-, di- and trifluoroacetic acid. Others suitable acids are benzoic acid, chlorbenzoic acid, methanesulfonic acid, ethanesulfonic acid, benzenesulfonic acid, p-toluenesulfonic acid, chlorbenzenesulfonic acid, trifluoromethanesulfonic acid, methylphosphonic acid or phenylphosphonic acid.

- 21 -

C₂-C₁₂alkanoyl is, for example, propionyl, butyryl, octanoyl, dodecanoyl, but preferably acetyl.

C₄-C₁₂alkenylene is, in particular, 2-butenylene, 2-pentenylene or 3-hexenylene.

C₆-C₁₂arylene is, for example, o-, m- or p-phenylene, 1,4-naphthylene or 4,4'-diphenylene.

The carboxylic acid radicals mentioned above are in each case taken to mean radicals of the formula $(-\text{CO})_x\text{R}$, where x is as defined above, and the meaning of R arises from the definition given.

C₁-C₁₈alkanoyloxy is, for example, formyloxy, acetyloxy, propionyloxy, butyryloxy, valeryloxy, lauroyloxy, palmitoyloxy and stearoyloxy.

A monovalent radical of a carboxylic acid is for example, an acetyl, caproyl, stearoyl, acryloyl, methacryloyl, benzoyl or β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl radical.

A monovalent silyl radical is for example, a radical of the formula


$-(\text{C}_j\text{H}_{2j})-\text{Si}(\text{Z}')_2\text{Z}''$, in which j is an integer in the range from 2 to 5, and Z' and Z'', independently of one another, are C₁-C₄alkyl or C₁-C₄alkoxy.

A divalent radical of a dicarboxylic acid, it is, for example, a malonyl, succinyl, glutaryl, adipoyl, suberoyl, sebacoyl, maleoyl, itaconyl, phthaloyl, dibutylmalonyl, dibenzylmalonyl, butyl(3,5-di-tert-butyl-4-hydroxybenzyl)malonyl or bicycloheptenedicarbonyl radical.

The nitroxyl radicals which are the precursors of the group A of formula (X) are known and may be prepared according to WO 99/03984, EP-A-0 891 986 or WO 98/13392.


Some typical examples are given below.

- 22 -



The nitroxyl radicals which are precursors of the group A of formula XXa, b and c are also known and may be prepared according to European Patent Application No. 98810741.3.

Typical examples are given below.



The nitroxyl radicals which are precursors of the group A of formula XXX are also known and can be prepared as described in European Patent Application No. 98810531.8.

- 23 -


Furthermore DE 26 21 841, US 4'131'599 and DE 26 30 798 for example describe the preparation of 2,6-diethyl-2,3,6-trimethyl-4-oxopiperidine and 2,6-dipropyl-3-ethyl-2,6-dimethyl-4-oxo-piperidine, which are intermediates for the corresponding 1-oxo compounds.

Another method for the preparation of 2,2-dimethyl-6,6-dialkyl-4-oxopiperidine is described by F. Asinger, M. Thiel, H. Baltz, Monatshefte für Chemie 88, 464 (1957) or by J. Bobbitt-et al. in J. Org. Chem. 58, 4837 (1993).


The oxidation of the piperidine compound to 1-oxo-piperidine derivatives is well known in the art and for example described by L.B. Volodarsky, V. A. Reznikov, V.I. Ovcharenko in Synthetic Chemistry of Stable Nitroxides, CRC Press, Boca Raton 1994.

The 2,2,6,6-tetramethylpiperidine precursors are known and partially commercially available.

Examples are given below.




- 24 -




The nitroxyl radicals which are precursors of the group A of formula XL are also known.

The compounds can be prepared according to WO 98/30601, WO 98/44008 or European Patent Application No. 98810741.3.

Some typical examples are given below.



- 25 -



Preferred compounds are those of formula (I) or (II), wherein A is a group of formula (X)

- 26 -

n_1 is 1

R_{101} is cyano;

R_{102} and R_{103} are each independently of one another unsubstituted C_1 - C_{12} alkyl or phenyl; or R_{102} and R_{103} , together with the linking carbon atom, form a C_5 - C_7 cycloalkyl radical;

R_{110} is C_4 - C_{12} alkyl bound via a tertiary C-atom to the nitrogen atom, C_9 - C_{11} phenylalkyl or phenyl; or

R_{110} and R_{111} together form a C_2 - C_6 alkylene bridge which is unsubstituted or substituted with C_1 - C_4 alkyl; and

R_{112} is C_1 - C_4 alkyl;

or wherein A is a group of formula (XXa)

R_{201} is tertiary C_4 - C_8 alkyl;

R_{202} and R_{203} are methyl, ethyl or together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{204} is C_1 - C_{18} alkoxy, benzyloxy or $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently of each other hydrogen or C_1 - C_8 alkyl;

or wherein A is a group of formula (XXb), wherein Q is O;

R_{205} , R_{206} , R_{207} and R_{208} are independently of each other methyl or ethyl; or

R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{209} and R_{210} are independently of each other formyl, C_2 - C_8 alkylcarbonyl, benzoyl, C_1 - C_8 alkyl, benzyl or phenyl;

or wherein A is a group of formula (XXc), wherein Y_1 is O;

R_{205} , R_{206} , R_{207} and R_{208} are independently of each other methyl or ethyl; or




R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{211} is formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, benzyl or phenyl and

R_{212} is OH, C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently of each other hydrogen or C_1 - C_{18} alkyl;

or wherein A is a group of formula (XXXA), (XXXB) or (XXXC);

- 27 -



wherein

G_1 , G_2 , G_3 and G_4 are independently alkyl of 1 to 4 carbon atoms, or G_1 and G_2 together and G_3 and G_4 together, or G_1 and G_2 together or G_3 and G_4 together are pentamethylene;

G_5 and G_6 are independently hydrogen or C_1 - C_4 alkyl;

m is a number from 1-4;

p is a number from 1-3;

R , if m is 1, is hydrogen, C_1 - C_{18} alkyl which is uninterrupted or C_2 - C_{18} alkyl which is interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid

- 28 -

having 7 to 15 carbon atoms, or an a,b-unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms, where each carboxylic acid can be substituted in the aliphatic, cycloaliphatic or aromatic moiety by 1 to 3 $-\text{COOZ}_{12}$ groups, in which Z_{12} is H, $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{12}$ alkenyl, $\text{C}_5\text{-C}_7$ cycloalkyl, phenyl or benzyl; or R is a monovalent radical of a carbamic acid or phosphorus-containing acid or a monovalent silyl radical;

R, if m is 2, is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_4\text{-C}_{12}$ alkenylene, xylylene, a divalent radical of an aliphatic dicarboxylic acid having 2 to 36 carbon atoms, or a cycloaliphatic or aromatic dicarboxylic acid having 8-14 carbon atoms or of an aliphatic, cycloaliphatic or aromatic dicarbamic acid having 8-14 carbon atoms, where each dicarboxylic acid may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by one or two $-\text{COOZ}_{12}$ groups; or

R is a divalent radical of a phosphorus-containing acid or a divalent silyl radical;

R, if m is 3, is a trivalent radical of an aliphatic, cycloaliphatic or aromatic tricarboxylic acid, which may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by $-\text{COOZ}_{12}$, of an aromatic tricarbamic acid or of a phosphorus-containing acid, or is a trivalent silyl radical,

R, if m is 4, is a tetravalent radical of an aliphatic, cycloaliphatic or aromatic tetracarboxylic acid;

p is 1, 2 or 3,

R_{401} is $\text{C}_1\text{-C}_{12}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl, $\text{C}_7\text{-C}_8$ aralkyl, $\text{C}_2\text{-C}_{18}$ alkanoyl, $\text{C}_3\text{-C}_5$ alkenoyl or benzoyl; when p is 1,

R_{402} is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl, $\text{C}_2\text{-C}_8$ alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula $-\text{CH}_2\text{CH}(\text{OH})-\text{Z}_4$ or of the formula $-\text{CO}-\text{Z}_4-$ or $-\text{CONH}-\text{Z}_4$ wherein Z_4 is hydrogen, methyl or phenyl; or when p is 2,


R_{402} is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_6\text{-C}_{12}$ -arylene, xylylene, a $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{-O-B-O-CH}_2\text{CH}(\text{OH})\text{CH}_2-$ group, wherein B is $\text{C}_2\text{-C}_{10}$ alkylene, $\text{C}_6\text{-C}_{15}$ arylene or $\text{C}_6\text{-C}_{12}$ cycloalkylene; or, provided that R_{401} is not alkanoyl, alkenoyl or benzoyl; or..

R_{402} is a divalent acyl radical of an aliphatic, cycloaliphatic or aromatic dicarboxylic acid or dicarbamic acid, or is the group $-\text{CO}-$; or..

R_{401} and R_{402} together when p is 1, can be the cyclic acyl radical of an aliphatic or aromatic 1,2- or 1,3-dicarboxylic acid; or

R_{402} is a group

- 29 -



where T_7 and T_8 are independently hydrogen, alkyl of 1 to 18 carbon atoms, or T_7 and T_8 together are alkylene of 4 to 6 carbon atoms or 3-oxapentamethylene;

when p is 3,

R_{402} is 2,4,6-triazinyl;

or wherein in formula (XLa) or (XLb)

R_{301} , R_{302} , R_{303} and R_{304} independently of each other are C_1 - C_3 alkyl, which is unsubstituted or substituted by OH, or a group $-O-C(O)-R_{305}$, or R_{301} and R_{302} and/or R_{303} and R_{304} together with the linking carbon atom form a C_5 - C_6 cycloalkyl radical;

R_{305} is hydrogen or C_1 - C_4 alkyl.

R_{306} and R_{307} independently are hydrogen, methyl or ethyl;

Z_1 is O or NR_{308} ;

Q_4 is a direct bond or a divalent radical CH_2 , CH_2CH_2 , $CH_2-CH_2-CH_2$, $C(O)$, $CH_2C(O)$ or $CH_2-CH-CH_3$;

R_{308} is hydrogen, C_1 - C_4 alkyl, C_1 - C_4 alkyl which is substituted by OH, or benzyl.

More preferred is a compound, wherein in formula (XXXA), (XXXB) or (XXXO) G_1 and G_3 are methyl and G_2 and G_4 are ethyl or propyl, or G_1 and G_2 are methyl and G_3 and G_4 are ethyl or propyl.


Particularly preferred is a compound of formula (XXXA) wherein G_1 and G_3 are methyl and G_2 and G_4 are ethyl or propyl, or G_1 and G_2 are methyl and G_3 and G_4 are ethyl or propyl, one of G_5 and G_6 is hydrogen and the other is methyl or both are hydrogen, m is 1 and R is C_1 - C_{18} alkyl or the monovalent radical of a C_2 - C_{18} carboxylic acid.

- 30 -


Preferably in formula (XLa) and (XLb) at least two of R_{301} , R_{302} , R_{303} and R_{304} are ethyl, propyl or butyl and the remaining are methyl and the other substituents have the meaning as defined above.

The compounds of the present invention can be prepared according to standard methods as illustrated in in examples A1-A18, which are however not comprehensive.


Particularly suitable starting materials are of formula (III), (IV) or (V)



(III)



(IV)



(V)

wherein:

R_1 , R_2 and A are as defined above;

Y is O, NR_3 or CHR_3 ; Halogen, and

Q_3 is hydrogen or $\text{C}_1\text{-C}_4$ alkyl.

Compounds according to formula (III), (IV) or (V) are also subject of the present invention.

The intermediate compounds (III) and IV) can be reacted according to known methods to yield compounds of formula (I) or (II).

A further subject of the present invention is a polymerizable composition, comprising

- a) at least one ethylenically unsaturated monomer or oligomer, and
- b) a compound of formula (I), (II), (III) or (IV).

Preferably b) is a compound of formula (I) or (II).

The definitions and preferences given above apply also for the composition.


Typically the ethylenically unsaturated monomer or oligomer is selected from the group consisting of ethylene, propylene, n-butylene, i-butylene, styrene, substituted styrene,

- 31 -

conjugated dienes, acrolein, vinyl acetate, vinylpyrrolidone, vinylimidazole, maleic anhydride, (alkyl)acrylic acidanhydrides, (alkyl)acrylic acid salts, (alkyl)acrylic esters, (meth)acrylonitriles, (alkyl)acrylamides, vinyl halides or vinylidene halides.


Preferred ethylenically unsaturated monomers are ethylene, propylene, n-butylene, i-butylene, isoprene, 1,3-butadiene, α -C₅-C₁₈alkene, styrene, α -methyl styrene, p-methyl styrene or a compound of formula $\text{CH}_2=\text{C}(\text{R}_a)-(\text{C}=\text{Z})-\text{R}_b$, wherein R_a is hydrogen or C₁-C₄alkyl, R_b is NH_2 , $\text{O}^-(\text{Me}^+)$, glycidyl, unsubstituted C₁-C₁₈alkoxy, C₂-C₁₀₀alkoxy interrupted by at least one N and/or O atom, or hydroxy-substituted C₁-C₁₈alkoxy, unsubstituted C₁-C₁₈alkylamino, di(C₁-C₁₈alkyl)amino, hydroxy-substituted C₁-C₁₈alkylamino or hydroxy-substituted di(C₁-C₁₈alkyl)amino, $-\text{O}-\text{CH}_2-\text{CH}_2-\text{N}(\text{CH}_3)_2$ or $-\text{O}-\text{CH}_2-\text{CH}_2-\text{N}^+\text{H}(\text{CH}_3)_2 \text{An}^-$; An^- is a anion of a monovalent organic or inorganic acid; Me is a monovalent metal atom or the ammonium ion. Z is oxygen or sulfur.

Examples for R_a as C₂-C₁₀₀alkoxy interrupted by at least one O atom are of formula



C_{18} alkyl, R_d is hydrogen or methyl and v is a number from 1 to 50. These monomers are for example derived from non ionic surfactants by acrylation of the corresponding alkoxyated alcohols or phenols. The repeating units may be derived from ethylene oxide, propylene oxide or mixtures of both.


Further examples of suitable acrylate or methacrylate monomers are given below.




and R_a have the meaning as defined above and R_e is methyl or benzyl. An^- is preferably Cl^- , Br^- or $^-\text{O}_3\text{S}-\text{CH}_3$.

- 32 -

Further acrylate monomers are



Examples for suitable monomers other than acrylates are



Preferably R_a is hydrogen or methyl; R_b is NH_2 , glycidyl, unsubstituted or with hydroxy substituted $\text{C}_1\text{-C}_4$ alkoxy, unsubstituted $\text{C}_1\text{-C}_4$ alkylamino, di($\text{C}_1\text{-C}_4$ alkyl)amino, hydroxy-substituted $\text{C}_1\text{-C}_4$ alkylamino or hydroxy-substituted di($\text{C}_1\text{-C}_4$ alkyl)amino; and Z is oxygen.

- 33 -

Particularly preferred ethylenically unsaturated monomers are styrene, methylacrylate, ethylacrylate, butylacrylate, isobutylacrylate, tert. butylacrylate, hydroxyethylacrylate, hydroxypropylacrylate, dimethylaminoethylacrylate, glycidylacrylates, methyl(meth)acrylate, ethyl(meth)acrylate, butyl(meth)acrylate, hydroxyethyl(meth)acrylate, hydroxypropyl(meth)acrylate, dimethylaminoethyl(meth)acrylate, glycidyl(meth)acrylates, acrylonitrile, acrylamide, methacrylamide or dimethylaminopropyl-methacrylamide.

It is also possible to enhance the rate of polymerization or copolymerization of slowly polymerizing monomers such as for example of the class of methacrylates, in particular methylmethacrylate by the addition of more readily polymerizable comonomers such as acrylates. Typical examples are the polymerization or copolymerization of methylmethacrylate in the presence of methylacrylate or butylacrylate.

Typical slowly polymerizing methacrylates are methyl(meth)acrylate, ethyl(meth)acrylate, butyl(meth)acrylate, hydroxyethyl(meth)acrylate, hydroxypropyl(meth)acrylate, dimethylaminoethyl(meth)acrylate, glycidyl(meth)acrylates, methacrylamide or dimethylaminopropyl-methacrylamide. The polymerization of these methacrylates can be enhanced by the addition of the corresponding acrylates.

Preferred is a composition, wherein the ethylenically unsaturated monomer is a mixture of a methacrylate and an acrylate.

The amounts of readily polymerizable comonomers range typically from 5 parts to 95 and the slowly polymerizable monomers range from 95 to 5 parts respectively.

The initiator/regulator compound of formula (I), (II), (III) or IV) is preferably present in an amount of from 0.01 mol-% to 30 mol-%, more preferably in an amount of from 0.01 mol-% to 20 mol-%, and most preferably in an amount of from 0.05 mol-% to 10 mol-% based on the monomer or monomer mixture.

A further subject of the invention is a process for preparing an oligomer, a cooligomer, a polymer or a copolymer (block or random) by free radical polymerization of at least one ethylenically unsaturated monomer or oligomer, which comprises (co)polymerizing the monomer or monomers/oligomers in the presence of an initiator/regulator compound of formula (I), (II), (III) or (IV) under reaction conditions capable of effecting scission of the O-C

- 34 -

bond to form two free radicals, the radical $\bullet\text{C}$ radical being capable of initiating polymerization.

The scission of the O-C bond can be effected by ultrasonic treatment, heating or exposure to electromagnetic radiation, ranging from γ to microwaves.

Preferably the scission of the O-C bond is effected by heating and takes place at a temperature of between 50°C and 160°C.

The process may be carried out in the presence of an organic solvent or in the presence of water or in mixtures of organic solvents and water. Additional cosolvents or surfactants, such as glycols or ammonium salts of fatty acids, may be present. Other suitable cosolvents are described hereinafter.

Preferred processes use as little solvents as possible. In the reaction mixture it is preferred to use more than 30% by weight of monomer and initiator, particularly preferably more than 50% and most preferably more than 80%. In many cases it is possible to polymerize without any solvent.

If organic solvents are used, suitable solvents or mixtures of solvents are typically pure alkanes (hexane, heptane, octane, isooctane), hydrocarbons (benzene, toluene, xylene), halogenated hydrocarbons (chlorobenzene), alkanols (methanol, ethanol, ethylene glycol, ethylene glycol monomethyl ether), esters (ethyl acetate, propyl, butyl or hexyl acetate) and ethers (diethyl ether, dibutyl ether, ethylene glycol dimethyl ether), or mixtures thereof.

The aqueous polymerization reactions can be supplemented with a water-miscible or hydrophilic cosolvent to help ensure that the reaction mixture remains a homogeneous single phase throughout the monomer conversion. Any water-soluble or water-miscible cosolvent may be used, as long as the aqueous solvent medium is effective in providing a solvent system which prevents precipitation or phase separation of the reactants or polymer products until after all polymerization reactions have been completed. Exemplary cosolvents useful in the present invention may be selected from the group consisting of aliphatic alcohols, glycols, ethers, glycol ethers, pyrrolidines, N-alkyl pyrrolidinones, N-alkyl pyrrolidones, polyethylene glycols, polypropylene glycols, amides, carboxylic acids and salts thereof, esters, organosulfides, sulfoxides, sulfones, alcohol derivatives, hydroxyether derivatives such as butyl carbitol or cellosolve, amino alcohols, ketones, and the like, as well

- 35 -

as derivatives thereof and mixtures thereof. Specific examples include methanol, ethanol, propanol, dioxane, ethylene glycol, propylene glycol, diethylene glycol, glycerol, dipropylene glycol, tetrahydrofuran, and other water-soluble or water-miscible materials, and mixtures thereof. When mixtures of water and water-soluble or water-miscible organic liquids are selected as the aqueous reaction media, the water to cosolvent weight ratio is typically in the range of about 100:0 to about 10:90.

The process is particularly useful for the preparation of block copolymers.

Block copolymers are, for example, block copolymers of polystyrene and polyacrylate (e.g., poly(styrene-co-acrylate) or poly(styrene-co-acrylate-co-styrene). They are useful as adhesives or as compatibilizers for polymer blends or as polymer toughening agents. Poly(methylmethacrylate-co-acrylate) diblock copolymers or poly(methylacrylate-co-acrylate-co-methacrylate) triblock copolymers) are useful as dispersing agents for coating systems, as coating additives (e.g. rheological agents, compatibilizers, reactive diluents) or as resin component in coatings (e.g. high solid paints) Block copolymers of styrene, (meth)acrylates and/or acrylonitrile are useful for plastics, elastomers and adhesives.

Furthermore, block copolymers of this invention, wherein the blocks alternate between polar monomers and non-polar monomers, are useful in many applications as amphiphilic surfactants or dispersants for preparing highly uniform polymer blends.

The (co)polymers of the present invention may have a number average molecular weight from 1 000 to 400 000 g/mol, preferably from 2 000 to 250 000 g/mol and, more preferably, from 2 000 to 200 000 g/mol. The number average molecular weight may be determined by size exclusion chromatography (SEC), gel permeation chromatography (GPC), matrix assisted laser desorption/ionization mass spectrometry (MALDI-MS) or, if the initiator carries a group which can be easily distinguished from the monomer(s), by NMR spectroscopy or other conventional methods.

The polymers or copolymers of the present invention have preferably a polydispersity of from 1.1 to 2, more preferably of from 1.2 to 1.8.

Thus, the present invention also encompasses in the synthesis novel block, multi-block, star, gradient, random, hyperbranched and dendritic copolymers, as well as graft copolymers.

The definitions and preferences for the different substituents given for the compounds, apply also for the composition and for the polymerization process.

The polymers prepared by the present invention are useful for following applications:

adhesives, detergents, dispersants, emulsifiers, surfactants, defoamers, adhesion promoters, corrosion inhibitors, viscosity improvers, lubricants, rheology modifiers, thickeners, crosslinkers, paper treatment, water treatment, electronic materials, paints, coatings, photography, ink materials, imaging materials, superabsorbants, cosmetics, hair products, preservatives, biocide materials or modifiers for asphalt, leather, textiles, ceramics and wood.

Because the present polymerization is a "living" polymerization, it can be started and stopped practically at will. Furthermore, the polymer product retains the functional alkoxyamine group allowing a continuation of the polymerization in a living matter. Thus, in one embodiment of this invention, once the first monomer is consumed in the initial polymerizing step a second monomer can then be added to form a second block on the growing polymer chain in a second polymerization step. Therefore it is possible to carry out additional polymerizations with the same or different monomer(s) to prepare multi-block copolymers.

Furthermore, since this is a radical polymerization, blocks can be prepared in essentially any order. One is not necessarily restricted to preparing block copolymers where the sequential polymerizing steps must flow from the least stabilized polymer-intermediate to the most stabilized polymer intermediate, such as is the case in ionic polymerization. Thus it is possible to prepare a multi-block copolymer in which a polyacrylonitrile or a poly(meth)acrylate block is prepared first, then a styrene or butadiene block is attached thereto, and so on.

Furthermore, there is no linking group required for joining the different blocks of the present block copolymer. One can simply add successive monomers to form successive blocks.

A plurality of specifically designed polymers and copolymers are accessible by the present invention, such as star and graft (co)polymers as described, inter alia, by C. J. Hawker in *Angew. Chemie*, 1995, 107, pages 1623-1627, dendrimers as described by K. Matyaszewski et al. in *Macromolecules* 1996, Vol 29, No. 12, pages 4167-4171, graft (co)polymers as described by C. J. Hawker et al. in *Macromol. Chem. Phys.* 198, 155-166(1997), random copolymers as described by C. J. Hawker in *Macromolecules* 1996, 29, 2686-2688, or

- 37 -

diblock and triblock copolymers as described by N. A. Listigovers in *Macromolecules* 1996, 29, 8992-8993.

Preferably a cooligomer or copolymer of star, comb or block structure is prepared.

Still further subjects of the invention are oligomer, cooligomer, polymer or copolymer prepared by said process and the use of a compound of formula (I) (II), (III) or (IV) for the polymerization of ethylenically unsaturated monomers.

The following examples illustrate the invention.

A Preparation of compounds

Example A1: (Compound 101)

A photoreactor is charged with 120 g (0.73 mol) of 4-ethylphenylacetate, 5 g (0.029 mol) of 4-hydroxy-2,2,6,6-tetramethylpiperidin-1-oxyl and 16.9 g (0.115 mol) of t-butylperoxide. The red solution is flushed with nitrogen and is then irradiated at 20-25°C using a mercury dipping lamp (Pyrex jacket). Subsequently, the reaction mixture is concentrated in a rotary evaporator and the residue is chromatographed over silica gel with hexane / ethyl acetate (6 : 4), affording 6.2 g (64% of theory) of compound 101 in the form of colourless crystals. m.p.: 65-67° C

Analysis calculated for $C_{19}H_{29}NO_4$: C 68.03%, H 8.71%, N 4.18%; found C 67.96%, H 8.85%, N 3.77%.

Example A2: (Compound 102)

5ml of HCl (37%) are added, with stirring and at room temperature, to a solution consisting of 10g (0.03 mol) of the compound 101 in 50 ml of methanol. After 30 minutes, the resulting residue is collected by filtration. The residue is slurried in water and the aqueous suspension is adjusted to pH 7-8 with solid sodium hydrogen carbonate and extracted with ether. The organic phase is then dried over Na_2SO_4 and concentrated in a rotary evaporator. The residue is recrystallised from toluene, affording 6.7 g (76 % of theory) of compound 102 in the form of white crystals. m.p.: 97-99 °C.

Analysis calculated for $C_{17}H_{27}NO_3$: C 69.59%, H 9.28%, N 4.77%; found C 70.36%, H 9.33%, N 4.48%.

Example A3: (Compound 103)

2.3 ml (0.027 mol) of allyl bromide are added dropwise at 20 °C to a suspension consisting of 4.0 g (0.014 mol) of compound 102 and 3.7 g (0.027 mol) of K_2CO_3 in 40 ml of acetone. This mixture is then stirred for 6 hours at 60 °C. The reaction mixture is filtered and the filtrate is then concentrated in a rotary evaporator. The residue is recrystallised from pentane, affording 2.6 g (58 % of theory) of compound 103 in the form of white crystals. m.p.: 66.5 - 67.5 °C.

Analysis calculated for $C_{20}H_{31}NO_3$: C 72.03%, H 9.37%, N 4.20%; found C 71.46%, H 9.36%, N 4.27%.

Example A4: (Compound 104)

A solution consisting of 22.0 g (0.075 mol) of compound 102 and 3 g (0.075) of NaOH in 30 ml of acetone and 50 ml of water is added dropwise at 5-10 °C to a solution consisting of 4.2 g (0.023 mol) of cyanuric chloride in 50 ml of acetone. After stirring the mixture for 16 hours at room temperature, the precipitated residue is collected by filtration. The filter cake is washed thoroughly with water, methanol and ether, affording 19.1 g (88% of theory) in the form of a white solid. m.p.: 212-214 °C.

Analysis calculated for $C_{54}H_{78}N_6O_9$: C 67.89%, H 8.23%, N 8.79%; found C 67.51%, H 8.24%, N 8.90%.

Example A5: (Compound 105)

In analogy to Example 3, 1 g (3.78 mmol) of α,α -dibromo-p-xylene, 2.45 g (8.35 mmol) of compound 102 and 1.15 g (8.32 mmol) of K_2CO_3 are reacted in 25 ml of acetone. The crude product is chromatographed over silica gel with methylene chloride / ethanol (10:2), giving 2.4 g (92% of theory) of compound 105 in the form of white crystals. m.p.: 139-141 °C.

Analysis calculated for $C_{42}H_{60}N_2O_6$: C 73.22%, H 8.78%, N 4.06%; found C 73.92%, H 8.57%, N 3.81%.

Example A6: (Compound 106)

In analogy to Example 3, 1 g (2.94 mmol) of 4,4'-bis(bromomethyl)biphenyl, 1.90 g (6.47 mmol) of compound 102 and 0.90 g (6.51 mmol) of K_2CO_3 are reacted in 20 ml of acetone. The crude product is chromatographed over silica gel with methylene chloride /

- 39 -

ethanol (10:2), giving 2.15 g (95% of theory) of compound 106 in the form of white crystals.

m.p.: 65-69° C

Analysis calculated for $C_{48}H_{64}N_2O_6$: C 75.35%, H 8.43%, N 3.66%; found C 74.51%, H 8.54%, N 3.40%.

Example A7: (Compound 107)

In analogy to Example 3, 5.0 g (0.011 mol) of 1,2,4,5-tetrakis(bromo-methyl)benzene, 15.0 g (0.051 mol) of compound 102 and 7.0 g (0.05 mol) of K_2CO_3 are reacted in 100 ml of acetone. The crude product is chromatographed over silica gel with methylene chloride / ethanol (10:3) and is then recrystallised from toluene, giving 9.1 g (63% of theory) of compound 107 in the form of white crystals. m.p.: 158-161 °C .

Analysis calculated for $C_{78}H_{114}N_4O_{12}$: C 72.08%, H 8.84%, N 4.31%; found C 71.53%, H 8.84%, N 3.99%.

Example A8: (Compound 108)

In analogy to Example 3, 5.0 g (7.86 mmol) of hexakis(bromomethyl)benzene, 15.6 g (53.1 mmol) of compound 102 and 7.4 g (53.5 mmol) of K_2CO_3 are reacted in 250 ml of acetone. The crude product is chromatographed over silica gel with methylene chloride / ethanol (10:3) and is then recrystallised from toluene, giving 13.3 g (89% of theory) of compound 108 in the form of white crystals. m.p.: 154-157 °C .

Analysis calculated for $C_{114}H_{168}N_6O_{18}$: C 71.66%, H 8.86%, N 4.39%; found C 71.64%, H 8.87%, N 4.06%.

Example A9: (Compound 109)

In analogy to Example 3, 1 ml (7.67 mmol) of ethyl 2-bromopropionate, 2.0 g (6.81 mmol) of compound 102 and 1.0 g (7.24 mmol) of K_2CO_3 are reacted in 10 ml of acetone. The crude product is chromatographed over silica gel with methylene chloride / ethanol (10:3), giving 2.25 g (84% of theory) of compound 109 in the form of a colourless oil.

Analysis calculated for $C_{22}H_{35}NO_5$: C 67.15%, H 8.96%, N 3.56%; found C 67.05%, H 8.99%, N 3.52%.

Example A10: (Compound 110)

In analogy to Example 1, compound 110 is obtained in the form of white crystals from 1-*t*-butyl-3,3-diethyl-5,5-dimethyl-piperazin-2-on-4-oxyl and 4-ethylphenylacetate. m.p.: 92-96

°C. Analysis calculated for $C_{24}H_{38}N_2O_4$: C 68.86%, H 15, N 6.69; found C 68.68%, H 9.10%, N 6.46%.

1-*t*-butyl-3,3-diethyl-5,5-dimethyl-piperazin-2-on-4-oxyl is prepared as described in EP Application No. 98811030.0.

Example A11: (Compound 111)

In analogy to Example 1, compound 111 is obtained in the form of white crystals from 1-*t*-butyl-3,3-diethyl-5,5-dimethyl-piperazin-2-on-4-oxyl and 4-ethylacetophenone. m.p.: 91-94 °C. Analysis calculated for $C_{24}H_{38}N_2O_3$: C 71.60%, H 9.51%, N 6.96%; found C %71.03, H 9.49%, N 6.90%.

1-*t*-butyl-3,3-diethyl-5,5-dimethyl-piperazin-2-on-4-oxyl is prepared as described in EP Application No. 98811030.0.

Example A12: (Compound 112)

A solution of 16 g of potassium carbonate is added dropwise at a temperature from 11-20 °C to a solution consisting of 32.3 g (0.077 mol) of compound 110 in 250 ml of methanol. After stirring for 15 minutes, the reaction mixture is acidified with 2N-HCl and diluted with 500 ml of water. The precipitated residue is collected by suction filtration, washed with water and dried, giving 28.4 g (96%) of compound 112 in the form of a beige microcrystalline powder, m.p. 145 - 147 °C.

$^1\text{H-NMR}$ (300 MHz, CDCl_3), $\delta(\text{ppm})$: (diastereomeric mixture): 7.17-6.76 m (4H), 4.65-4.54 m (1H), 3.14-2.93 m (2H), 2.13-0.55 m (28H).

Example A13: (Compound 113)

In analogy to Example 3, 2.64 g (0.01 mol) of *a,a'*-dibromo-*p*-xylene, 7.9 g (0.021 mol) of compound 112 and 2.8 g (0.02 mol) of K_2CO_3 are reacted in 30 ml of acetone. The crude product is chromatographed over silica gel with ethyl acetate / hexane (1:4), giving 4.4 g (51% of theory) of compound 113 in the form of a colourless resin.

Analysis calculated for $\text{C}_{52}\text{H}_{78}\text{N}_4\text{O}_6$: C 73.03%, H 9.19%, N 6.55%; found C 73.17%, H 9.19%, N 6.55%.

Example A14: (Compound 114)

In analogy to Example 3, 2.25 g (0.005 mol) of 1,2,4,5-tetrakis(bromomethyl)benzene, 7.9 g (0.021 mol) of compound 112 and 2.8 g (0.02 mol) of K_2CO_3 are reacted in 40 ml of acetone.

The crude product is chromatographed over silica gel with hexane / *t*-butylmethyl ether (3:1) and is then recrystallised from hexane, giving 5.1 g (62.5% of theory) of compound 114 in the form of white crystals. m.p.: 148-153 °C .

¹H-NMR (300 MHz, CDCl₃), δ(ppm): (diastereomeric mixture): 7.64 s (2H), 7.16-6.83 m (16H), 5.10 s (8H), 4.61-4.57 m (4H), 3.05-2.80 m (8H), 2.07-0.57 m (112H).

Example A15: (Compound 115)

In analogy to Example 3, 2.12 g (0.003 mol) of hexakis(bromomethyl)benzene, 7.9 g (0.021 mol) of compound 112 and 2.8 g (0.02mol) of K₂CO₃ are reacted in 40 ml of acetone. The crude product is chromatographed over silica gel with hexane / ethyl acetate (4:1), giving 7.55 g (95% of theory) of compound 115 in the form of a colourless resin.

¹H-NMR (300 MHz, CDCl₃), δ(ppm): (diastereomeric mixture): 7.24-6.84 m (24H), 5.20 bs (12H), 4.65-4.63 m (6H), 3.12-2.88 m (12H), 2.13 -0.65 m (168H).

Example A16: (Compound 116)

3.1 ml (0.06 mol) of bromine are added dropwise, with cooling, to a solution consisting of 8 g (0.2 mol) of NaOH in 60 ml water, keeping the temperature below 10 °C. A solution consisting of 8.05 g (0.02 mol) of compound 111 in 25 ml dioxane is then added dropwise and the mixture is stirred for 5 hours at a temperature from 10-20 °C. Subsequently, 100 ml of water are added and the solution is extracted with 50 ml of methyl-*t*-butyl ether. The aqueous phase is acidified with HCl and extracted again with 2x50 ml of methyl-*t*-butyl ether. These extracts are then washed with water, dried over MgSO₄ and concentrated by evaporation. The residue is slurried in hexane, filtered and dried, giving 6.55 g (81%) of compound 116 in the form of a beige microcrystalline powder, m.p. 172-177 °C.

¹H-NMR (300 MHz, CDCl₃), δ(ppm): (diastereomeric mixture): 7.15 d (2H), 7.35 d (2H), 4.73-4.71 m (1H), 3.16-2.83 m (2H), 2.11 -0.60 m (28H).

Example A17: (Compound 117)

5.75 g (0.014 mol) of compound 116, 0.1g of 4-dimethylaminopyridine, 1.31 g (0.0065 mol) of 1,12-dodecanediol and 2.95 g (0.014 mol) of dicyclohexylcarbodiimide are stirred in 25 ml of dichloromethane for 20 hours. After filtering the reaction mixture, the filtrate is chromatographed over silica gel with ethyl acetate / hexane (5:1), giving 4.95 g (78%) of compound 117 in the form of a colourless resin.

- 42 -

Analysis calculated for $C_{58}H_{94}N_4O_8$: C 71.42%, H 9.71%, N 5.74%; found C 71.33%, H 9.66%, N 5.79%.





Example A18: (Compound 118)

In analogy to Example 117, 4.7 g (70%) of compound 118 are obtained in the form of a colourless resin from 7.1 g (0.00176 mol) of compound 116, 0.55 g (0.004 mol) of pentaerythritol, 0.1 g of 4-dimethylaminopyridine and 3.63g (0.00176 mol) of dicyclohexylcarbodiimide in 25 ml of dichloromethane.




$^1\text{H-NMR}$ (300 MHz, CDCl_3), $\delta(\text{ppm})$: (diastereomeric mixture): 7.91 d (8H), 7.28 d (8H), 4.83-4.76 m (4H), 4.73 bs (8H), 3.16-2.91 m (8H), 2.19 -0.69 m (112H).

The compounds prepared are summarised in Table 1.





Table 1





No.	Verbindung
101	
102	
103	
104	

- 44 -




105	
106	
107	

- 45 -

108	
109	
110	
111	

112	 <p>Chemical structure of a cyclic oxazolidinone derivative. It features a five-membered ring with a nitrogen atom (N) and an oxygen atom (O). The nitrogen is substituted with a tert-butyl group and a methyl group. The oxygen is substituted with a 4-hydroxyphenyl group. The ring also contains a carbonyl group (C=O) and a methyl group.</p>
113	 <p>Chemical structure of a bis-oxazolidinone derivative. It consists of two oxazolidinone rings connected by a central biphenyl group. Each oxazolidinone ring is substituted with a tert-butyl group, a methyl group, and a carbonyl group. The biphenyl group is connected to the rings via ether linkages.</p>
114	 <p>Chemical structure of a tetra-oxazolidinone derivative. It features a central benzene ring substituted with four ether linkages, each connecting to an oxazolidinone ring. Each oxazolidinone ring is substituted with a tert-butyl group, a methyl group, and a carbonyl group.</p>
11	 <p>Chemical structure of a hexa-oxazolidinone derivative. It features a central benzene ring substituted with six ether linkages, each connecting to an oxazolidinone ring. Each oxazolidinone ring is substituted with a tert-butyl group, a methyl group, and a carbonyl group.</p>

- 47 -

116	 <p>Chemical structure of a polyimide containing a p-phenylene-4-carboxylic acid moiety. The structure shows a repeating unit of a polyimide with a central benzene ring substituted with a carboxylic acid group (HO-C(=O)-) and a polyimide chain.</p>
117	 <p>Chemical structure of a polyimide containing a long aliphatic spacer. The structure shows a repeating unit of a polyimide with a central benzene ring substituted with a long aliphatic chain (O-C(=O)-C₁₂H₂₄-C(=O)-O-) and a polyimide chain.</p>
118	 <p>Chemical structure of a polyimide containing a complex branched structure. The structure shows a repeating unit of a polyimide with a central benzene ring substituted with a complex branched structure (O-C(=O)-C₆H₄-C(=O)-O-) and a polyimide chain.</p>

- 48 -

Polymerization examples

B) Polymerization of styrene with compounds 104, 105, 107 and 108

Reaction conditions: Schlenk flask, 50 ml styrene, Ar-purged

Regulator: amount of regulator corresponds to amount of styrene (50 ml=0,436 mol).

Table 2

Compound	No.	Temp.(°C)	Time (Hrs.)	amount of regulator	Conv. (%)	M _n	M _w	M _w /M _n
104	B1	130	6	0,33 mol%	51	13400	16900	1,26
104	B2	130	6	0,033 mol%	59	77500	140800	1,82
105	B3	130	6	0,33 mol%	(42)	11400	14900	1,30
105	B4	130	6	0,033 mol%	(62)	76700	124600	1,62
107	B5	120	6	0,33 mol%	(25)	6200	7800	1,26
107	B6	130	6	0,33 mol%	(57)	11600	17400	1,49
107	B7	120	6	0,033 mol%	(39)	5900	8900	1,51

- 49 -

107	B8	130	6	0,033 mol%	(72)	75000	148500	1,98
108	B9	130	6	0,33 mol%	(34)	7200	11500	1,61

C Polymerization of acrylates

Example C1

A 50ml round-bottom three-necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 0.441 g (1.17 mmol) of compound 112 and 10 g (78 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 5 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 4 g (40%) of the monomer are reacted and a colorless viscous liquid is obtained.

GPC : Mn=4500, Mw=5600, Polydispersity index = 1.25

Example C2

A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 1.601 g (1.872 mmol) of compound 113 and 8 g (62.4 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 3 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 5.68 g (71%) of the monomer are reacted and a clear yellow viscous liquid is obtained.

GPC : Mn=4300, Mw=4900, Polydispersity index = 1.15

Example C3

A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 1.528 g (0.936 mmol) of compound 114 and 8 g (62.4 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 3 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 5.2 g (65%) of the monomer are reacted and a clear yellow viscous liquid is obtained.

GPC : Mn=8500, Mw=9700, Polydispersity index = 1.15

Example C4

A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 2.255 g (0.936 mmol) of compound 115 and 8 g (62.4 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon.

- 51 -

The mixture is stirred for 3 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 4.8 g (60%) of the monomer are reacted and a yellow viscous liquid is obtained.

GPC : Mn=7400, Mw=8100, Polydispersity index = 1.1

Example C5

A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 0.473 g (1.17 mmol) of compound 116 and 10 g (78 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 5 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 8.6 g (86%) of the monomer are reacted and a colorless viscous liquid is obtained.

GPC : Mn=8100, Mw=12000, Polydispersity index = 1.5

Example C6

A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 1.826 g (1.872 mmol) of compound 117 and 8 g (62.4 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 3 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 5.2 g (65%) of the monomer are reacted and a clear yellow viscous liquid is obtained.

GPC : Mn=4700, Mw=5500, Polydispersity index = 1.2

Example C7


A 50ml round-bottom three necked flask, equipped with thermometer, condenser and magnetic stirrer is charged with 1.575 g (0.936 mmol) of compound 118 and 8 g (62.4 mmol) of n-Butylacrylate and degassed. The clear solution is then heated to 145°C under argon. The mixture is stirred for 3 hours at 145°C and then cooled to 60°C and the remaining monomer is evaporated under high vacuum. 5.2 g (65%) of the monomer are reacted and a clear yellow viscous liquid is obtained.

GPC : Mn=8400, Mw=9600, Polydispersity index = 1.15


THIS PAGE BLANK (USPTO)

Claims

1. A compound of formula (I) or (II)



(I)



(II)

wherein

R_1 and R_2 are independently of each other hydrogen, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkynyl or phenyl which are unsubstituted or substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

A is a group capable of forming a stable free nitroxyl radical $A\bullet$, which is bound via its oxygen atom to the carbon atom;

Y is O, NR_3 or CHR_3-X_a , wherein X_a is O, S or NR_3 ;

R_3 is hydrogen, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkynyl or phenyl which are unsubstituted or substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, C_1 - C_4 alkoxy, C_1 - C_4 alkylthio, C_1 - C_4 alkylamino or di(C_1 - C_4 alkyl)amino;

Q_1 is an organic or inorganic radical, derived from a compound having at least one functional group being capable of reacting with a hydroxy group;

Q_2 is an organic radical derived from a mono or polyfunctional alcohol, mono or polyfunctional aminoalcohol, mono or polyfunctional amine mono or polyfunctional mercaptane, mono or polyfunctional phenol or mono or polyfunctional thiophenol; and


n is a number from 1 to 20;

with the proviso, that if R_1 is H and R_2 is $-CH_2-O$ -tert.butyl, A is not 2,2,6,6-tetramethylpiperidine or 2,2,6,6-tetramethylpiperidine-4-carboxylic acid.

2. A compound of formula (I), wherein Q_1 is derived from an unsubstituted or substituted triazine, from a mono or multifunctional alkylating agent, from a mono or polycarboxylic acid or acid derivative, from a mono or polyepoxide, from a mono or polyisocyanate or from $POCl_3$, SO_2Cl_2 , BCl_3 or $SiCl_4$.

3. A compound of formula (I) or (II) according to claim 1, wherein R_1 and R_2 are independently of each other hydrogen, C_1 - C_{12} alkyl, C_3 - C_{12} alkenyl or phenyl.
4. A compound of formula (II) according to claim 1, wherein Y is O or NR_3 .
5. A compound of formula (I) or (II) according to claim 1, wherein n is a number from 2-10.
6. A compound of formula (I) according to claim 1, wherein Q_1 is an organic radical derived from an unsubstituted or substituted triazine, from a mono or polycarboxylic acid or acid derivative, from a mono or multifunctional alkylating agent or from a mono or polyisocyanate.
7. A compound of formula (I) according to claim 6, wherein Q_1 is an organic radical derived from an unsubstituted or substituted triazine, from a polycarboxylic acid or polycarboxylic acid derivative, having 2-6 carboxyl groups, from a multifunctional alkylating agent having 2-6 functional groups, or from a polyisocyanate, having 2-6 isocyanate groups.
8. A compound of formula (II) according to claim 1, wherein Q_2 is an organic radical derived from a polyfunctional alcohol, a polyfunctional aminoalcohol or a polyfunctional amine.
9. A compound of formula (II) according to claim 8, wherein Q_2 is a radical derived from a polyalcohol having 2-6 hydroxy groups, a polyaminoalcohol having 2-6 amino and/or hydroxy groups, or a polyamine having 2-6 amine groups.
10. A compound of formula (I) or (II) according to claim 1, wherein the radical $A \cdot$ derived from the group A is a stable open chain nitroxyl radical or a cyclic nitroxyl radical.
11. A compound of formula (I) or (II) according to claim 1, wherein A is a group of formula (X)

- 54 -



wherein n_1 is 0 or 1

R_{101} , R_{102} , R_{103} are each independently of one another hydrogen, halogen, NO_2 , cyano, $-\text{CONR}_{105}\text{R}_{106}$, $-(\text{R}_{109})\text{COOR}_{104}$, $-\text{C}(\text{O})-\text{R}_{107}$, $-\text{OR}_{108}$, $-\text{SR}_{108}$, $-\text{NHR}_{108}$, $-\text{N}(\text{R}_{108})_2$, carbamoyl, $\text{di}(\text{C}_1\text{-C}_{18}\text{alkyl})\text{carbamoyl}$, $-\text{C}(=\text{NR}_{105})(\text{NHR}_{106})$; unsubstituted $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkenyl}$, $\text{C}_2\text{-C}_{18}\text{alkynyl}$, $\text{C}_7\text{-C}_9\text{phenylalkyl}$, $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ or $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ containing at least one nitrogen or oxygen atom; or $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkenyl}$, $\text{C}_2\text{-C}_{18}\text{alkynyl}$, $\text{C}_7\text{-C}_9\text{phenylalkyl}$, $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ or $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ containing at least one nitrogen or oxygen atom, which are substituted by NO_2 , halogen, amino, hydroxy, cyano, carboxy, $\text{C}_1\text{-C}_4\text{alkoxy}$, $\text{C}_1\text{-C}_4\text{alkylthio}$, $\text{C}_1\text{-C}_4\text{alkylamino}$ or $\text{di}(\text{C}_1\text{-C}_4\text{alkyl})\text{amino}$; or phenyl, which is unsubstituted or substituted by $\text{C}_1\text{-C}_4\text{alkyl}$, $\text{C}_1\text{-C}_4\text{alkoxy}$, $\text{C}_1\text{-C}_4\text{alkylthio}$, halogen, cyano, hydroxy, carboxy, $\text{C}_1\text{-C}_4\text{alkylamino}$ or $\text{di}(\text{C}_1\text{-C}_4\text{alkyl})\text{amino}$; or R_{102} and R_{103} , together with the linking carbon atom, form a $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ radical, a $(\text{C}_4\text{-C}_{12}\text{cycloalkanon})\text{-yl}$ radical or a $\text{C}_3\text{-C}_{12}\text{cycloalkyl}$ radical containing at least one O atom and/or a NR_{108} group; or if n_1 is 1



R_{104} is hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$, phenyl, an alkali metal cation or a tetraalkylammonium cation; R_{105} and R_{106} are hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$, $\text{C}_2\text{-C}_{18}\text{alkyl}$ which is substituted by at least one hydroxy group or, taken together, form a $\text{C}_2\text{-C}_{12}\text{alkylene}$ bridge or a $\text{C}_2\text{-C}_{12}\text{-alkylene}$ bridge interrupted by at least one O or/and NR_{108} atom; R_{107} is hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$ or phenyl; R_{108} is hydrogen, $\text{C}_1\text{-C}_{18}\text{alkyl}$ or $\text{C}_2\text{-C}_{18}\text{alkyl}$ which is substituted by at least one hydroxy group; R_{109} is $\text{C}_1\text{-C}_{12}\text{alkylene}$ or a direct bond;

R₁₁₀ is C₄-C₁₈alkyl bound via a tertiary C-atom to the nitrogen atom, C₉-C₁₁phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or C₄-C₁₈alkyl bound via a tertiary C-atom to the nitrogen atom, C₉-C₁₁phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; if n₁ is 1

R₁₁₁ is C₁-C₁₈alkyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or C₁-C₁₈alkyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or a polycyclic cycloaliphatic ring system or a polycyclic cycloaliphatic ring system with at least one di- or trivalent nitrogen atom; or

R₁₁₀ and R₁₁₁ together form a C₂-C₁₂alkylene bridge, a C₃-C₁₂alkylen-on-bridge or a C₂-C₁₂alkylene bridge which is interrupted by at least one O or N-atom; which bridges are unsubstituted or substituted with C₁-C₁₈alkyl, hydroxy(C₁-C₄)alkyl, phenyl, C₇-C₉phenylalkyl, NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino,




R₁₁₂ is hydrogen, -(R₁₀₉)COOR₁₀₄, cyano, -OR₁₀₈, -SR₁₀₈, -NHR₁₀₈, -N(R₁₀₈)₂, -NH-C(O)-R₁₀₈, unsubstituted C₁-C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom; or

C₁-C₁₈alkyl, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₇-C₉phenylalkyl, C₃-C₁₂cycloalkyl or C₃-C₁₂cycloalkyl containing at least one nitrogen or oxygen atom, which are substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino; or

phenyl, naphthyl, which are unsubstituted or substituted by C₁-C₄alkyl, C₁-C₄alkoxy, C₁-C₄alkylthio, halogen, cyano, hydroxy, carboxy, C₁-C₄alkylamino, di(C₁-C₄alkyl)amino; or R₁₁₁ and R₁₁₂ together with the linking carbon atom form a C₃-C₁₂cycloalkyl radical;

or A is a group of formula XXa, XXb or XXc

- 56 -



wherein

Y_1 is O or CH_2 ;

Q is O or NR_{220} , wherein R_{220} is hydrogen or C_1 - C_{18} alkyl;

R_{201} is tertiary C_4 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$ wherein R_{221} is hydrogen, a alkali metal atom or C_1 - C_{18} alkyl and R_{222} is C_1 - C_{18} alkyl; or

R_{201} is C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, a polycyclic alkyl radical or a polycyclic alkyl radical which is interrupted by at least one O or N atom;

R_{202} and R_{203} are independently C_1 - C_{18} alkyl, benzyl, C_5 - C_{12} cycloalkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$ or together with the carbon atom form a C_5 - C_{12} cycloalkyl ring;

if Y_1 is O,

R_{204} and R_{212} are OH, O(alkali-metal) C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently from each other hydrogen, C_1 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

if Y_1 is CH_2 ,

R_{204} is OH, C_1 - C_{18} alkoxy, benzyloxy, $O-C(O)-(C_1-C_{18})$ alkyl or $NR_{223}R_{224}$;

R_{212} are a group $C(O)R_{225}$, wherein R_{225} is OH, C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently from each other hydrogen, C_1 - C_{18} alkyl or phenyl, which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;


R_{205} , R_{206} , R_{207} and R_{208} are independently of each other C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl or phenyl; or

R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_{12} cycloalkyl ring;

R_{209} and R_{210} are independently of each other hydrogen, formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, benzyl or phenyl which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$;

R_{211} , is formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl, C_5 - C_{12} cycloalkyl which is interrupted by at least one O or N atom, benzyl or phenyl which are unsubstituted or substituted by halogen, OH, $COOR_{221}$ or $C(O)-R_{222}$.

or A is a group containing a structural element of formula (XXX)





G_1 , G_2 , G_3 , G_4 are independently C_1 - C_6 alkyl or G_1 and G_2 or G_3 and G_4 or G_1 and G_2 and G_3 and G_4 together form a C_5 - C_{12} cycloalkyl group;

G_5 , G_6 independently are H, C_1 - C_{18} alkyl, phenyl, naphthyl or a group $COOC_1$ - C_{18} alkyl;

- 58 -

or A is a group of formula (XLa) or (XLb)



R_{301} , R_{302} , R_{303} and R_{304} independently of each other are C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by OH, halogen or a group $-O-C(O)-R_{305}$, C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_{305} group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl or R_{301} and R_{302} and/or R_{303} and R_{304} together with the linking carbon atom form a C_3 - C_{12} cycloalkyl radical;

R_{305} , R_{306} and R_{307} independently are hydrogen, C_1 - C_{18} alkyl or C_6 - C_{10} aryl;

Z_1 is O or NR_{308} ;

R_{308} is hydrogen, OH, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl, C_1 - C_{18} alkyl, C_3 - C_{18} alkenyl, C_3 - C_{18} alkinyl which are substituted by one or more OH, halogen or a group $-O-C(O)-R_{305}$, C_2 - C_{18} alkyl which is interrupted by at least one O atom and/or NR_{305} group, C_3 - C_{12} cycloalkyl or C_6 - C_{10} aryl, C_7 - C_9 phenylalkyl, C_5 - C_{10} heteroaryl, $-C(O)-C_1$ - C_{18} alkyl, $-O-C_1$ - C_{18} alkyl or $-COOC_1$ - C_{18} alkyl;

Q_4 is a direct bond or a divalent radical $CR_{309}R_{310}$, $CR_{309}R_{310}-CR_{311}R_{312}$,

$CR_{309}R_{310}CR_{311}R_{312}CR_{313}R_{314}$, $C(O)$ or $CR_{309}R_{310}C(O)$, wherein R_{309} , R_{310} , R_{311} , R_{312} , R_{313} and R_{314} are independently hydrogen, phenyl or C_1 - C_{18} alkyl.

12. A compound of formula (I) or (II) according to claim 11, wherein A is a group of formula (X)

n_1 is 1

R_{101} is cyano;

R_{102} and R_{103} are each independently of one another unsubstituted C_1 - C_{12} alkyl or phenyl;
or R_{102} and R_{103} , together with the linking carbon atom, form a C_5 - C_7 cycloalkyl radical;
 R_{110} is C_4 - C_{12} alkyl bound via a tertiary C-atom to the nitrogen atom, C_9 - C_{11} phenylalkyl or phenyl; or

R_{110} and R_{111} together form a C_2 - C_6 alkylene bridge which is unsubstituted or substituted with C_1 - C_4 alkyl; and

R_{112} is C_1 - C_4 alkyl;

or wherein A is a group of formula (XXa)

R_{201} is tertiary C_4 - C_8 alkyl;

R_{202} and R_{203} are methyl, ethyl or together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{204} is C_1 - C_{18} alkoxy, benzyloxy or $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently of each other hydrogen or C_1 - C_8 alkyl;

or wherein A is a group of formula (XXb); wherein Q_1 is O;

R_{205} , R_{206} , R_{207} and R_{208} are independently of each other methyl or ethyl; or

R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{209} and R_{210} are independently of each other formyl, C_2 - C_8 alkylcarbonyl, benzoyl, C_1 - C_8 alkyl, benzyl or phenyl;

or wherein A is a group of formula (XXc), wherein Y_1 is O;

R_{205} , R_{206} , R_{207} and R_{208} are independently of each other methyl or ethyl; or




R_{205} and R_{206} and/or R_{207} and R_{208} together with the carbon atom form a C_5 - C_6 cycloalkyl ring;

R_{211} is formyl, C_2 - C_{18} alkylcarbonyl, benzoyl, C_1 - C_{18} alkyl, benzyl or phenyl and

R_{212} is OH, C_1 - C_{18} alkoxy, benzyloxy, $NR_{223}R_{224}$, wherein R_{223} and R_{224} are independently of each other hydrogen or C_1 - C_{18} alkyl.

or wherein A is a group of formula (XXXA), (XXXB) or (XXXC).

- 60 -



wherein

G_1 , G_2 , G_3 and G_4 are independently alkyl of 1 to 4 carbon atoms, or G_1 and G_2 together and G_3 and G_4 together, or G_1 and G_2 together or G_3 and G_4 together are pentamethylene;
 G_5 and G_6 are independently hydrogen or C_1 - C_4 alkyl;

m is a number from 1-4;

p is a number from 1-3;

R , if m is 1, is hydrogen, C_1 - C_{18} alkyl which is uninterrupted or C_2 - C_{18} alkyl which is interrupted by one or more oxygen atoms, cyanoethyl, benzoyl, glycidyl, a monovalent radical of an aliphatic carboxylic acid having 2 to 18 carbon atoms, of a cycloaliphatic carboxylic acid

having 7 to 15 carbon atoms, or an a,b-unsaturated carboxylic acid having 3 to 5 carbon atoms or of an aromatic carboxylic acid having 7 to 15 carbon atoms, where each carboxylic acid can be substituted in the aliphatic, cycloaliphatic or aromatic moiety by 1 to 3 $-\text{COOZ}_{12}$ groups, in which Z_{12} is H, $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{12}$ alkenyl, $\text{C}_5\text{-C}_7$ cycloalkyl, phenyl or benzyl; or R is a monovalent radical of a carbamic acid or phosphorus-containing acid or a monovalent silyl radical;

R, if m is 2, is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_4\text{-C}_{12}$ alkenylene, xylylene, a divalent radical of an aliphatic dicarboxylic acid having 2 to 36 carbon atoms, or a cycloaliphatic or aromatic dicarboxylic acid having 8-14 carbon atoms or of an aliphatic, cycloaliphatic or aromatic dicarbamic acid having 8-14 carbon atoms, where each dicarboxylic acid may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by one or two $-\text{COOZ}_{12}$ groups; or

R is a divalent radical of a phosphorus-containing acid or a divalent silyl radical;

R, if m is 3, is a trivalent radical of an aliphatic, cycloaliphatic or aromatic tricarboxylic acid, which may be substituted in the aliphatic, cycloaliphatic or aromatic moiety by $-\text{COOZ}_{12}$, of an aromatic tricarbamic acid or of a phosphorus-containing acid, or is a trivalent silyl radical,

R, if m is 4, is a tetravalent radical of an aliphatic, cycloaliphatic or aromatic tetracarboxylic acid;

p is 1, 2 or 3,

R_{401} is $\text{C}_1\text{-C}_{12}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl, $\text{C}_7\text{-C}_8$ aralkyl, $\text{C}_2\text{-C}_{18}$ alkanoyl, $\text{C}_3\text{-C}_5$ alkenoyl or benzoyl; when p is 1,

R_{402} is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_7$ cycloalkyl, $\text{C}_2\text{-C}_8$ alkenyl unsubstituted or substituted by a cyano, carbonyl or carbamide group, or is glycidyl, a group of the formula $-\text{CH}_2\text{CH}(\text{OH})-\text{Z}_4$ or of the formula $-\text{CO}-\text{Z}_4-$ or $-\text{CONH}-\text{Z}_4$ wherein Z_4 is hydrogen, methyl or phenyl; or

when p is 2,


R_{402} is $\text{C}_2\text{-C}_{12}$ alkylene, $\text{C}_6\text{-C}_{12}$ -arylene, xylylene, a $-\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{-O-B-O-CH}_2\text{CH}(\text{OH})\text{CH}_2-$ group, wherein B is $\text{C}_2\text{-C}_{10}$ alkylene, $\text{C}_6\text{-C}_{15}$ arylene or $\text{C}_6\text{-C}_{12}$ cycloalkylene; or, provided that R_{401} is not alkanoyl, alkenoyl or benzoyl; or

R_{402} is a divalent acyl radical of an aliphatic, cycloaliphatic or aromatic dicarboxylic acid or dicarbamic acid, or is the group $-\text{CO}-$; or

R_{401} and R_{402} together when p is 1 can be the cyclic acyl radical of an aliphatic or aromatic 1,2- or 1,3-dicarboxylic acid; or

R_{402} is a group

- 62 -



where T_7 and T_8 are independently hydrogen, alkyl of 1 to 18 carbon atoms, or T_7 and T_8 together are alkylene of 4 to 6 carbon atoms or 3-oxapentamethylene;

when p is 3,

R_{402} is 2,4,6-triazinyl;

or wherein in formula (XLa) or (XLb)

R_{301} , R_{302} , R_{303} and R_{304} independently of each other are C_1 - C_3 alkyl, which is unsubstituted or substituted by OH, or a group $-O-C(O)-R_{305}$, or R_{301} and R_{302} and/or R_{303} and R_{304} together with the linking carbon atom form a C_5 - C_6 cycloalkyl radical;

R_{305} is hydrogen or C_1 - C_4 alkyl.

R_{306} and R_{307} independently are hydrogen, methyl or ethyl;

Z_1 is O or NR_{308} ;

Q_4 is a direct bond or a divalent radical CH_2 , CH_2CH_2 , $CH_2-CH_2-CH_2$, $C(O)$, $CH_2C(O)$ or $CH_2-CH-CH_3$;


R_{308} is hydrogen, C_1 - C_4 alkyl, C_1 - C_4 alkyl which is substituted by OH, or benzyl.

13. A compound according to claim 11, wherein in formula (XXXA), (XXXB) or (XXXO) G_1 and G_3 are methyl and G_2 and G_4 are ethyl or propyl, or G_1 and G_2 are methyl and G_3 and G_4 are ethyl or propyl.


14. A compound according to claim 11, wherein in formula (XXXA) G_1 and G_3 are methyl and G_2 and G_4 are ethyl or propyl, or G_1 and G_2 are methyl and G_3 and G_4 are ethyl or propyl, one of G_5 and G_6 is hydrogen and the other is methyl or both are hydrogen, m is 1 and R is C_1 - C_{18} alkyl or the monovalent radical of a C_2 - C_{18} carboxylic acid.

15. A compound according to claim 11 wherein in formula (XLa) and (XLb) at least two of R_{301} , R_{302} , R_{303} and R_{304} are ethyl, propyl or butyl and the remaining are methyl.


16. A compound of formula (III), (IV) or (V)



(III)



(IV)



(V)

wherein

R₁, R₂ and A are as defined in claim 1;

Y is O, NR₃ or CHR₃-Halogen; and

Q₃ is hydrogen or C₁-C₄alkyl.

17. A polymerizable composition, comprising

a) at least one ethylenically unsaturated monomer or oligomer; and

b) a compound of formula (I), (II), (III) or (IV) according to claim 1.

18. A polymerizable composition according to claim 16; wherein b) is a compound of formula (I) or (II).

19. A process for preparing an oligomer, a cooligomer, a polymer or a copolymer (block or random) by free radical polymerization of at least one ethylenically unsaturated monomer or oligomer, which comprises (co)polymerizing the monomer or monomers/oligomers in the presence of an initiator/regulator compound of formula (I), (II), (III) or (IV), according to claim 1 or 15 under reaction conditions capable of effecting scission of the O-C bond to form two free radicals, the radical •C radical being capable of initiating polymerization.

20. A process according to claim 19, wherein the scission of the O-C bond is effected by ultrasonic treatment; heating or exposure to electromagnetic radiation, ranging from γ to microwaves.

21. A process according to claim 19, wherein the scission of the O-C bond is effected by heating and takes place at a temperature of between 50°C and 160°C.

- 64 -

22. A process according to claim 19, wherein a cooligomer or copolymer of star, comb or block structure is prepared.

23. A process according to claim 19, wherein the compound of formula (I), (II), (III) or (IV) is present in an amount of 0.01 to 30 weight % based on the monomer or monomer mixture.


24. A oligomer, cooligomer, polymer or copolymer prepared by a process according to claim 19.

25. Use of a compound of formula (I) (II), (III) or (IV) according to claim 1 or 16 for the polymerization of ethylenically unsaturated monomers.


THIS PAGE BLANK (USPTO)

Summary

The invention pertains to a compound of formula (I) or (II)



(I)



(II)

wherein

R₁ and R₂ are independently of each other hydrogen, C₁-C₁₈alkyl, C₃-C₁₈alkenyl, C₃-C₁₈alkinyl or phenyl which are unsubstituted or substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

A is a group capable of forming a stable free nitroxyl radical A•, which is bound via its oxygen atom to the carbon atom;

Y is O, NR₃ or CHR₃-X_a, wherein X_a is O, S or NR₃;

R₃ is hydrogen, C₁-C₁₈alkyl, C₃-C₁₈alkenyl, C₃-C₁₈alkinyl or phenyl which are unsubstituted or substituted by NO₂, halogen, amino, hydroxy, cyano, carboxy, C₁-C₄alkoxy, C₁-C₄alkylthio, C₁-C₄alkylamino or di(C₁-C₄alkyl)amino;

Q₁ is an organic or inorganic radical, derived from a compound having at least one functional group being capable of reacting with a hydroxy group;

Q₂ is an organic radical derived from a mono or polyfunctional alcohol, mono or polyfunctional aminoalcohol, mono or polyfunctional amine mono or polyfunctional mercaptane, mono or polyfunctional phenol or mono or polyfunctional thiophenol; and

n is a number from 1 to 20;

with the proviso, that if R₁ is H and R₂ is -CH₂-O-tert.butyl, A is not 2,2,6,6-tetramethylpiperidine or 2,2,6,6-tetramethylpiperidine-4-carboxylic acid.

Further subjects of the invention are a composition comprising above compounds and at least one ethylenically unsaturated monomer, process for polymerization and the (co)polymers obtained therefrom.

THIS PAGE BLANK (USPTO)